BS EN 14319-2:2013



BSI Standards Publication

Thermal insulating products for building equipment and industrial installations — In-situ formed dispensed rigid polyurethane (PUR) and polyisocyanurate foam (PIR) products Part 2: Specification for the installed insulation products

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW



raising standards worldwide[™]

National foreword

This British Standard is the UK implementation of EN 14319-2:2013.

The UK participation in its preparation was entrusted to Technical Committee PRI/72, Rigid cellular materials.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013.

ISBN 978 0 580 53440 9

ICS 91.100.60

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2013.

Amendments issued since publication

Date Text affected

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 14319-2

January 2013

ICS 91.100.60

English Version

Thermal insulating products for building equipment and industrial installations - In-situ formed dispensed rigid polyurethane (PUR) and polyisocyanurate foam (PIR) products - Part 2: Specification for the installed insulation products

Produits isolants thermiques destinés aux équipements de bâtiment et aux installations industrielles - Produits en mousse rigide de polyuréthanne (PUR) et de polyisocyanurate (PIR) injectée, formés en place - Partie 2: Spécifications relatives aux produits isolants après mise en œuvre Wärmedämmstoffe für die technische Gebäudeausrüstung und für betriebstechnische Anlagen in der Industrie - An der Verwendungsstelle hergestellter Wärmedämmstoff aus Polyurethan (PUR) und Polyisocyanurat (PIR)-Gießschaum - Teil 2: Spezifikation für die eingebauten Produkte

This European Standard was approved by CEN on 24 November 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Ref. No. EN 14319-2:2013: E

Contents

Foreword			
1	Scope	.4	
2	Normative references	.4	
3 3.1 3.2	Terms, definitions, symbols and abbreviations Terms and definitions Symbols and abbreviations	.4 .4 .6	
4 4.1 4.2	Requirements General Suitability of the building equipment or industrial installation for the installation of the product	.6 .6 .6	
5 5.1 5.2 5.3	In-situ measurements and calculations Declared installed insulation thickness Declared installed thermal resistance, $R_{\rm D}$ Foam quality checks carried out by the installer	.6 .6 .6 .7	
6	Guidelines for installation	.7	
7	Installer's declaration	.7	
Annex A (normative) Method for the determination of the declared installed insulation thickness8			
Annex B.1 B.2	B (normative) Suitability of the building equipment or industrial installation to receive the insulation product Building equipment or industrial installation	.9 .9 .9	
Annex C.1 C.2 C.3 C.3.1 C.3.2 C.4	C (normative) Installation guidelines General Suitability of cavity Dispensing machine preparation General Mixing ratio Dispensing procedure	10 10 10 10 10 10	
Bibliog	Bibliography11		

Foreword

This document (EN 14319-2:2013) has been prepared by Technical Committee CEN/TC 88 "Thermal insulating materials and products", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2013, and conflicting national standards shall be withdrawn at the latest by July 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This European Standard consists of two parts which form a package. The first part is the harmonised part satisfying the mandate and the CPD and which is the basis for the CE marking covering the products, which are placed on the market. The second part, which is the non-harmonised part, covers the specification for the installed products. Both parts need to be used for the application of the insulation products in the end-use applications covered by EN 14319.

Attention is drawn to the need to take into account any complementary member state rules (e.g. installation rules) which together with Part 2 of this European Standard ensures the fitness for purpose of the installed product.

This European Standard is one of a series for expanded perlite, exfoliated vermiculite and polyurethane/polyisocyanurate in-situ formed insulation products used in building equipment and industrial installations, but this standard may be used in other areas where appropriate.

The reduction in energy used and emissions produced during the installed life of insulation products exceeds by far the energy used and emissions made during the production and disposal processes.

EN 14319, Thermal insulating products for building equipment and industrial installations — In-situ formed dispensed rigid polyurethane (PUR) and polyisocyanurate foam (PIR) products consists of the following parts:

— Part 1: Specification for the rigid foam dispensed system

— Part 2: Specification for the installed insulation products (the present document)

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies requirements for in-situ formed dispensed polyurethane (PUR) and polyisocyanurate (PIR) foam products for the insulation of building equipment industrial installations, for example storage vessels, pipes and ducts used for the supply of fuels, oil, other liquids, hot and cold water, air and other gases.

Depending on the type of foam products complying with this standard, they may have service temperature ranges which lie within the limits of \pm 200 °C.

This Part 2 of this European Standard is a specification for the installed insulation product.

This Part 2 of this European Standard describes, when taken together with Part 1 of EN 14319, the product characteristics that are linked to the essential requirements of the EU Construction Products Directive. It also specifies the checks and tests to be used for the declarations made by the installer of the product.

This European Standard does not specify the required levels of all properties to be achieved by a product to demonstrate fitness for purpose in a particular application. The required levels are to be found in regulations or non-conflicting standards.

This European Standard does not cover factory made rigid polyurethane (PUR) or polyisocyanurate (PIR) foam products or in-situ products intended to be used for the insulation of buildings.

The products are not intended for use for direct airborne sound insulation or acoustic absorption applications.

NOTE Foam products are either called flexible or rigid. The flexible products are used in upholstery and mattresses and are characterised by their ability to deflect, support and recover to their original thickness continually during their inuse phase. Those that are not flexible are termed rigid and do not possess these flexible characteristics. They are mostly used for thermal insulation purposes and vary widely in their compression strength values. Once the cell structure is crushed in a rigid foam, it does not recover its thickness fully. Some of these rigid foams are very low in density with very low compression strengths and are sometimes described "commercially" as "soft foams" or "semi-rigid" foams. This note has been included to clarify that all foams with such descriptions are covered by this standard's used of the term rigid foam.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 14319-1:2013, Thermal insulating products for building equipment and industrial installations — In-situ formed dispensed rigid polyurethane (PUR) and polyisocyanurate foam (PIR) products — Part 1: Specification for the rigid foam dispensed system

EN ISO 9229:2007, Thermal insulation — Vocabulary (ISO 9229:2007)

3 Terms, definitions, symbols and abbreviations

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 9229:2007 and the following apply.

3.1.1

polyurethane foam PUR

(in-situ formed products)

rigid cellular plastics insulation material or product with a structure based on polymers mainly of the polyurethane type