

BS EN 60317-47:2014



BSI Standards Publication

# Specifications for particular types of winding wires

Part 47: Aromatic polyimide enamelled rectangular copper wire, class 240

**bsi.**

...making excellence a habit.™

### **National foreword**

This British Standard is the UK implementation of EN 60317-47:2014. It is identical to IEC 60317-47:2013. It supersedes BS EN 60317-47:1997 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee GEL/55, Winding wires.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014.  
Published by BSI Standards Limited 2014

ISBN 978 0 580 75959 8  
ICS 29.060.10

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2014.

### **Amendments/corrigenda issued since publication**

<b>Date</b>	<b>Text affected</b>
-------------	----------------------

---

English version

**Specifications for particular types of winding wires -  
Part 47: Aromatic polyimide enamelled rectangular copper wire, class 240  
(IEC 60317-47:2013)**

Spécifications pour types particuliers de  
fils de bobinage -  
Partie 47: Fil de section rectangulaire en  
cuivre émaillé avec polyimide aromatique,  
classe 240  
(CEI 60317-47:2013)

Technische Lieferbedingungen für  
bestimmte Typen von Wickeldrähten -  
Teil 47: Flachdrähte aus Kupfer,  
lackisoliert mit aromatischen Polyimiden,  
Klasse 240  
(IEC 60317-47:2013)

This European Standard was approved by CENELEC on 2013-11-18. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

**CENELEC**

European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

**CEN-CENELEC Management Centre: Avenue Marnix 17, B - 1000 Brussels**

## Foreword

The text of document 55/1421/FDIS, future edition 2 of IEC 60317-47, prepared by IEC/TC 55 "Winding wires" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 60317-47:2014.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2014-08-18
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2016-11-18

This document supersedes EN 60317-47:1997.

EN 60317-47:2014 includes the following significant technical changes with respect to EN 60317-47:1997:

- deletion of the "in some countries" statement in the scope;
- new subclause containing general notes on winding wire, formerly a part of the scope;
- new subclause containing requirements for appearance;
- revision to the notes in Clause 19, Dielectric dissipation factor;
- new Clause 23, Pin hole test.

This standard is to be read in conjunction with EN 60317-0-2:2014.

The numbering of clauses in this standard is not continuous from Clauses 20 and 30 in order to reserve space for possible future wire requirements prior to those for wire packaging.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

## Endorsement notice

The text of the International Standard IEC 60317-47:2013 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

IEC 60264 Series	NOTE	Harmonized as EN 60264 Series (not modified).
IEC 60317 Series	NOTE	Harmonized as EN 60317 Series (not modified).
IEC 60851 Series	NOTE	Harmonized as EN 60851 Series (not modified).

**Annex ZA**  
(normative)

**Normative references to international publications  
with their corresponding European publications**

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60317-0-2	2013	Specifications for particular types of winding wires - Part 0-2: General requirements - Enamelled rectangular copper wire	EN 60317-0-2	2014

## CONTENTS

INTRODUCTION .....	5
1 Scope .....	6
2 Normative reference .....	6
3 Terms, definitions, general notes, and appearance .....	6
3.1 Terms and definitions .....	6
3.2 General notes .....	6
3.2.1 Methods of test .....	6
3.2.2 Winding wire .....	6
3.3 Appearance .....	7
4 Dimensions .....	7
5 Electrical resistance .....	7
6 Elongation .....	7
7 Springiness .....	7
8 Flexibility and adherence .....	7
9 Heat shock .....	7
10 Cut-through .....	7
11 Resistance to abrasion .....	7
12 Resistance to solvents .....	7
13 Breakdown voltage .....	7
14 Continuity of insulation .....	8
15 Temperature index .....	8
16 Resistance to refrigerants .....	8
17 Solderability .....	8
18 Heat or solvent bonding .....	8
19 Dielectric dissipation factor .....	8
20 Resistance to transformer oil .....	8
21 Loss of mass .....	8
23 Pin hole test .....	8
30 Packaging .....	8
Bibliography .....	9

## INTRODUCTION

This part of IEC 60317 is one of a series of standards which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) Winding wires – Test methods (IEC 60851);
- 2) Specifications for particular types of winding wires (IEC 60317);
- 3) Packaging of winding wires (IEC 60264).

## SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

### Part 47: Aromatic polyimide enamelled rectangular copper wire, class 240

#### 1 Scope

This part of IEC 60317 specifies the requirements of enamelled rectangular copper winding wire of class 240 with a sole coating of aromatic polyimide resin.

The range of nominal conductor dimensions covered by this standard is:

- width:           min. 2,0 mm       max. 16,0 mm;
- thickness:       min. 0,80 mm      max. 5,60 mm.

Wires of grade 1 and grade 2 are included in this specification and apply to the complete range of conductors.

The specified combinations of width and thickness, as well as the specified width/thickness ratio, are given in IEC 60317-0-2.

#### 2 Normative reference

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60317-0-2:2013, *Specifications for particular types of winding wires – Part 0-2: General requirements – Enamelled rectangular copper wire*

#### 3 Terms, definitions, general notes, and appearance

##### 3.1 Terms and definitions

Subclause 3.1 of IEC 60317-0-2:2013 applies.

##### 3.2 General notes

###### 3.2.1 Methods of test

Subclause 3.2.1 of IEC 60317-0-2:2013 applies. In case of inconsistencies between IEC 60317-0-2: 2013 and this standard, the latter shall prevail.

###### 3.2.2 Winding wire

Class 240 is a thermal class that requires a minimum temperature index of 240 and heat shock temperature of at least 260 °C.

The temperature in degrees Celsius corresponding to the temperature index is not necessarily that at which it is recommended that the wire be used, and this will depend on many factors, including the type of equipment involved.