
**Steel and cast iron — Determination
of copper — 2,2'-Biquinoline
spectrophotometric method**

*Aciers et fontes — Détermination du cuivre — Méthode
spectrophotométrique au 2,2'-biquinolyle*



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	1
5 Apparatus	2
6 Sampling	2
7 Procedure	3
7.1 Test portion.....	3
7.2 Blank test.....	3
7.3 Determination.....	3
7.3.1 Preparation of the test solution.....	3
7.3.2 Colour development.....	3
7.3.3 Preparation of the compensating solution.....	4
7.3.4 Spectrophotometric measurement.....	4
7.4 Establishment of the calibration graph.....	4
7.4.1 Preparation of the calibration solutions.....	4
7.4.2 Spectrophotometric measurement.....	4
7.4.3 Calibration graph.....	4
8 Expression of results	5
9 Precision	5
9.1 General.....	5
9.2 Repeatability.....	6
9.3 Reproducibility.....	6
10 Test report	6
Annex A (informative) Additional information on the international interlaboratory test	7
Annex B (informative) Graphical representation of precision data	8
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#).

The committee responsible for this document is ISO/TC 17, *Steel*, Subcommittee SC 1, *Methods of determination of chemical composition*.

This second edition cancels and replaces the first edition (ISO 4946:1984), which has been technically revised to include the following changes:

- correction of the specification of plotting the calibration graphs in [7.4.3](#);
- editorial revision of some items in accordance with the updated ISO/IEC Directives, Part 2.

Steel and cast iron — Determination of copper — 2,2'-Biquinoline spectrophotometric method

1 Scope

This International Standard specifies a spectrophotometric method for the determination of copper in steel and cast iron by 2,2'-biquinoline.

The method is applicable to the determination of copper mass fraction in the range of 0,02 % and 5 %.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

3 Principle

Dissolution of a test portion in appropriate acids.

Fuming with perchloric acid to remove hydrochloric and nitric acids and dehydrate silicic acid.

Reduction of copper(II) to copper(I) in hydrochloric acid solution by means of ascorbic acid. Formation of a coloured compound of copper(I) with 2,2'-biquinoline.

Spectrophotometric measurement at a wavelength of about 545 nm.

4 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only grade 2 water as specified in ISO 3696.

4.1 High-purity iron, containing copper 0,001 % (mass fraction) or less.

4.2 Hydrochloric acid, ρ approximately 1,19 g/ml.

4.3 Nitric acid, ρ approximately 1,40 g/ml.

4.4 Perchloric acid, ρ approximately 1,54 g/ml.

WARNING — Perchloric acid vapour might cause explosions in the presence of ammonia, nitrous fumes or organic material in general.