

---

---

**Plastics — Differential scanning  
calorimetry (DSC) —**

**Part 3:  
Determination of temperature and  
enthalpy of melting and crystallization**

*Plastiques — Analyse calorimétrique différentielle (DSC) —*

*Partie 3: Détermination de la température et de l'enthalpie de fusion  
et de cristallisation*





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Apparatus and materials</b> .....	<b>2</b>
<b>6 Test specimen</b> .....	<b>2</b>
<b>7 Test conditions and specimen conditioning</b> .....	<b>2</b>
<b>8 Calibration</b> .....	<b>2</b>
<b>9 Procedure</b> .....	<b>2</b>
9.1 Setting up the apparatus.....	2
9.2 Loading the test specimen into the crucible.....	2
9.3 Insertion of crucibles.....	2
9.4 Temperature scan.....	2
<b>10 Expression of results</b> .....	<b>3</b>
10.1 Determination of transition temperatures.....	3
10.2 Determination of enthalpies.....	4
<b>11 Precision</b> .....	<b>5</b>
<b>12 Test report</b> .....	<b>5</b>
<b>Bibliography</b> .....	<b>6</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This third edition cancels and replaces the second edition (ISO 11357-3:2011), which has been technically revised. The main changes compared to the previous edition are as follows:

- the normative references in [Clause 2](#) have been updated;
- the sample mass is referring to polymer matrix;
- the procedure has been extended to cover materials with wider crystallisation ranges;
- the calculation of heats of transition has been clarified to include computer aided methods.

A list of all parts in the ISO 11357 series can be found on the ISO website.

# Plastics — Differential scanning calorimetry (DSC) —

## Part 3:

# Determination of temperature and enthalpy of melting and crystallization

## 1 Scope

This document specifies a method for the determination of the temperatures and enthalpies of melting and crystallization of crystalline or partially crystalline plastics.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472 and ISO 11357-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

### 3.1

#### **melting**

transition stage between a fully crystalline or partially crystalline solid state and an amorphous liquid of variable viscosity

Note 1 to entry: The transition, also referred to as “fusion”, is characterized by an endothermic peak in the DSC curve. An exception to this definition is the case of liquid crystals, where the term “amorphous liquid” is replaced by “ordered liquid”.

### 3.2

#### **crystallization**

transition stage between an amorphous liquid state and a fully crystalline or partially crystalline solid state

Note 1 to entry: The transition is characterized by an exothermic peak in the DSC curve. An exception to this definition is the case of liquid crystals, where the term “amorphous liquid” is replaced by “ordered liquid”.

### 3.3

#### **enthalpy of fusion**

heat required to melt a material at constant pressure

Note 1 to entry: It is expressed in kilojoules per kilogram (kJ/kg) or joules per gram (J/g).