

INTERNATIONAL
STANDARD

ISO
20863

Second edition
2018-03

Footwear — Test methods for stiffeners and toepuffs — Bondability

*Chaussures — Méthodes d'essai pour contreforts et bouts-durs —
Aptitude au collage*



Reference number
ISO 20863:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus and materials	1
5 Sampling and conditioning	2
5.1 Method 1: Heat activated materials	2
5.2 Method 2: Solvent activated materials	2
6 Procedure	3
7 Expression of results	3
7.1 Dry bondability	3
7.2 Wet bondability	4
8 Test report	4
Bibliography	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 216, *Footwear*.

This second edition cancels and replaces the first edition (ISO 20863:2004), which has been technically revised.

Footwear — Test methods for stiffeners and toepuffs — Bondability

1 Scope

This document specifies a method for the determination of the bondability of heat activated and solvent activated stiffeners and toepuffs to upper and lining materials.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system*

ISO 18454, *Footwear — Standard atmospheres for conditioning and testing of footwear and components for footwear*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

bondability

aptitude of a material to be bonded to itself or to other material by applying pressure and/or heat and eventually adhesive

4 Apparatus and materials

The following apparatus and materials shall be used:

4.1 Tensile testing machine, with a jaw separation rate of 100 mm/min \pm 10 mm/min, an appropriate force range (this will usually be less than 100 N), capable of measuring the force to an accuracy of better than 2 % as specified by class 2 in ISO 7500-1, which registers the force applied in terms of the displacement.

4.2 Press knife, or other means of cutting rectangular test specimens of (150 mm \pm 10 mm) \times (30 mm \pm 2 mm).

4.3 Press, with the following characteristics:

4.3.1 Heated plates, which can maintain a pre-established temperature with an accuracy of ± 5 °C.