

FINAL VERSION

VERSION FINALE



**Winding wires – Test methods –
Part 5: Electrical properties**

**Fils de bobinage – Méthodes d'essai –
Partie 5: Propriétés électriques**

CONTENTS

1	Scope	7
2	Normative references	7
3	Test 5: Electrical resistance.....	7
4	Test 13: Breakdown voltage	8
4.1	Principle	8
4.2	Equipment	8
4.3	Enamelled round wire	9
4.3.1	Grade 1 to grade 3 with a nominal diameter up to and including 0,100 mm	9
4.3.2	Grade of FIW 3 to FIW 9 with a nominal conductor diameter up to and including 1,600 mm.....	10
4.4	Enamelled round wire with a nominal conductor diameter over 0,100 mm up to and including 2,500 mm, grade 1 to grade 3	11
4.4.1	Test at room temperature	11
4.4.2	Test at elevated temperature	12
4.5	Round wire with a nominal conductor diameter over 2,500 mm.....	13
4.5.1	Test at room temperature	13
4.5.2	Test at elevated temperature	15
4.6	Fibre wound round wire	15
4.6.1	Test at room temperature	15
4.6.2	Test at elevated temperature	16
4.7	Rectangular wire	17
4.7.1	Test at room temperature	17
4.7.2	Test at elevated temperature	17
5	Test 14: Continuity of insulation (applicable to enamelled round and tape wrapped round wire).....	17
5.1	General	17
5.2	Low-voltage continuity (nominal conductor diameter up to and including 0,050 mm, grade 1 to grade 3)	18
5.3	High-voltage continuity (nominal conductor diameter over 0,050 mm up to and including 1,600 mm, grade 1 to grade 3, and over 0,035 mm, up to and including 1,600 mm, grade 3 of FIW 3 to FIW 9).....	19
5.3.1	Principle	19
5.3.2	Equipment	19
5.3.3	Procedure.....	24
5.3.4	Result.....	25
5.4	Inline high-voltage continuity (wires in accordance with grade of FIW 3 to FIW 10 with nominal conductor diameter over 0,035 mm up to and including 1,600 mm).....	25
5.4.1	Principle	25
5.4.2	Equipment	26
5.4.3	Procedure.....	26
5.4.4	Result.....	27
6	Test 19: Dielectric dissipation factor (applicable to enamelled wire and bunched wire).....	27
6.1	Principle	27
6.2	Equipment	28
6.3	Specimen	29

6.3.1	Specimen for a metal bath electrode.....	29
6.3.2	Specimen for a conductive suspension electrode.....	29
6.4	Procedure	29
6.5	Result	29
7	Test 23: Pin hole test.....	29
Annex A (informative)	Dissipation factor methods	31
A.1	Tangent delta – Intersection point	31
A.2	Test methods	31
A.2.1	Method A.....	31
A.2.2	Method B – Wire coated with a conductive film	32
A.3	Interpretation of results	32
A.3.1	General	32
A.3.2	Linear method	32
A.3.3	Logarithmic method	33
Figure 1	– Arrangement of cylinder and specimen for the breakdown voltage test.....	10
Figure 2	– Device for twisting the specimen for breakdown voltage test.....	12
Figure 3	– U-bend specimen for the breakdown voltage test (specimen placed in shot bath).....	14
Figure 4	– Coil-wound specimen for the breakdown voltage test	16
Figure 5	– Apparatus for testing the low-voltage continuity of covering	18
Figure 6	– High-voltage d.c. continuity – Pulleys for wire size 0,050 mm to 0,250 mm	20
Figure 7	– Pulley dimensions and spacing for wire size 0,250 mm to 1,600 mm	21
Figure 8a	– Graphite fibre single brush electrode assembly	22
Figure 8b	– Graphite fibre dual brush electrode assembly.....	23
Figure 8	– Graphite fibre single or dual brush electrode assembly.....	23
Figure 9	– Suitable electrode arrangement for testing the dielectric dissipation factor.....	28
Figure A.1	– Example of linear method for sole coating.....	33
Figure A.2	– Example of logarithmic method for sole coating	33
Table 1	– Rates of test voltage increase	8
Table 2.1	– Loads applied to the wire	9
Table 2.2	– Loads and diameters of test cylinders applied to wire	11
Table 3	– Loads applied to the wire and number of twists	12
Table 4	– Off-line HVC fault currents	20
Table 5.1	– Off-line HVC test voltages for grades 1 – 3.....	24
Table 5.2	– Off-line HVC test voltages for grade of FIW 3 – FIW 9.....	25
Table 7	– In-line HVC test voltages.....	27

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**WINDING WIRES –
TEST METHODS –****Part 5: Electrical properties**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

DISCLAIMER

This Consolidated version is not an official IEC Standard and has been prepared for user convenience. Only the current versions of the standard and its amendment(s) are to be considered the official documents.

This Consolidated version of IEC 60851-5 bears the edition number 4.2. It consists of the fourth edition (2008-07) [documents 55/1069/FDIS and 55/1078/RVD], its amendment 1 (2011-06) [documents 55/1223/FDIS and 55/1251/RVD] and its amendment 2 (2019-09) [documents 55/1791/FDIS and 55/1818/RVD]. The technical content is identical to the base edition and its amendments.

This Final version does not show where the technical content is modified by amendments 1 and 2. A separate Redline version with all changes highlighted is available in this publication.

International Standard IEC 60851-5 has been prepared by IEC technical committee 55: Winding wires.

Significant revisions to the previous edition include the following points:

- in Subclause 5.3, the addition of the use of carbon brush electrodes for the counting discontinuities during the high voltage continuity test, as an alternative to the V-groove pulley electrode;
- clarifications in the breakdown voltage test for round wires larger than 2,500 mm and for fibrous covered wires.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60851 series, under the general title *Winding wires – Test methods*, can be found on the website.

The amendment 1 includes

- in Clause 4 the addition of dielectric breakdown requirements for fully insulated (FIW) zero-defect enamelled round copper wires;
- in Clause 5 the addition of continuity requirements for fully insulated (FIW) zero-defect enamelled round copper wires.

The committee has decided that the contents of the base publication and its amendments will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

This part of IEC 60851 forms an element of a series of standards which deals with insulated wires used for windings in electrical equipment. The series has three groups describing

- a) winding wires – Test methods (IEC 60851);
- b) specifications for particular types of winding wires (IEC 60317);
- c) packaging of winding wires (IEC 60264).

WINDING WIRES – TEST METHODS –

Part 5: Electrical properties

1 Scope

This part of IEC 60851 specifies the following tests:

- Test 5: Electrical resistance;
- Test 13: Breakdown voltage;
- Test 14: Continuity of insulation;
- Test 19: Dielectric dissipation factor;
- Test 23: Pin hole.

For definitions, general notes on methods of test and the complete series of methods of test for winding wires, see IEC 60851-1.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60851-1, *Winding wires – Test methods – Part 1: General*

3 Test 5: Electrical resistance

Electrical resistance is the d.c. resistance at 20 °C of 1 m of wire.

The method used shall provide a precision of 0,5 %.

For bunched wires a length of up to 10 m shall be used and the ends shall be soldered before the measurement. When measuring the resistance to check for an excessive number of broken wires, a length of 10 m of bunched wire shall be used.

If the resistance R_t is measured at a temperature t other than 20 °C, the resistance R_{20} at 20 °C shall be calculated by means of the following formula:

$$R_{20} = \frac{R_t}{1 + \alpha (t - 20)}$$

where

t is the actual temperature in degrees Celsius during the measurement;

α is the temperature coefficient in K⁻¹.