

BS IEC 60317-4:2015



BSI Standards Publication

Specifications for particular types of winding wires

Part 4: Solderable polyurethane enamelled round copper wire, class 130

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of IEC 60317-4:2015. It supersedes BS EN 60317-4:1995 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee L/-99, Miscellaneous Standards - Electrical.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2015.

Published by BSI Standards Limited 2015

ISBN 978 0 580 83424 0

ICS 29.060.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2015.

Amendments/corrigenda issued since publication

Date	Text affected
-------------	----------------------



INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Specifications for particular types of winding wires –
Part 4: Solderable polyurethane enamelled round copper wire, class 130**

**Spécifications pour types particuliers de fils de bobinage –
Partie 4: Fil brasable de section circulaire en cuivre émaillé avec polyuréthane,
classe 130**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.060.10

ISBN 978-2-8322-2729-9

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Terms, definitions, general notes and appearance.....	6
3.1 Terms and definitions.....	6
3.2 General notes.....	6
3.2.1 Methods of test.....	6
3.2.2 Winding wire.....	6
3.2.3 Appearance.....	7
4 Dimensions.....	7
5 Electrical resistance.....	7
6 Elongation.....	7
7 Springiness.....	7
8 Flexibility and adherence.....	7
9 Heat shock.....	7
10 Cut-through.....	7
11 Resistance to abrasion (nominal conductor diameters from 0,250 mm up to and including 2,000 mm).....	7
12 Resistance to solvents.....	8
13 Breakdown voltage.....	8
14 Continuity of insulation.....	8
15 Temperature index.....	8
16 Resistance to refrigerants.....	8
17 Solderability.....	8
17.1 Nominal conductor diameters up to and including 0,100 mm.....	8
17.2 Nominal conductor diameter over 0,100 mm.....	9
18 Heat or solvent bonding.....	9
19 Dielectric dissipation factor.....	9
20 Resistance to transformer oil.....	9
21 Loss of mass.....	9
23 Pin hole test.....	9
30 Packaging.....	9
Bibliography.....	10
Table 1 – Resistance to abrasion.....	8

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –**Part 4: Solderable polyurethane enamelled round copper wire, class 130**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60317-4 has been prepared by IEC technical committee 55: Winding wires.

This fourth edition cancels and replaces the third edition published in 1990, Amendment 1:1997 and Amendment 2:1999. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- new 3.2.2 containing general notes on winding wire, formerly a part of the scope;
- new 3.2.3 containing requirements for appearance;
- revision to references to IEC 60317-0-1:2013 to clarify that their application is normative;
- consolidation of 17.1 and 17.2 of the solderability requirements;
- revision to Clause 19, dielectric dissipation factor;
- new Clause 23, pin hole test.

The text of this standard is based on the following documents:

CDV	Report on voting
55/1459/CDV	55/1498/RVC

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

This International Standard is to be read in conjunction with IEC 60317-0-1:2013.

The numbering of clauses in this standard is not continuous from Clauses 20 and 30 in order to reserve space for possible future wire requirements prior to those for wire packaging.

A list of all parts in the IEC 60317 series, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

This part of IEC 60317 is one of a series which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) Winding wires – Test methods (IEC 60851 series);
- 2) Specifications for particular types of winding wires (IEC 60317 series);
- 3) Packaging of winding wires (IEC 60264 series).

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 4: Solderable polyurethane enamelled round copper wire, class 130

1 Scope

This part of IEC 60317 specifies the requirements of solderable enamelled round copper winding wire of class 130 with a sole coating based on polyurethane resin, which may be modified provided it retains the chemical identity of the original resin and meets all specified wire requirements.

NOTE A modified resin is a resin that has undergone a chemical change, or contains one or more additives to enhance certain performance or application characteristics.

The range of nominal conductor diameters covered by this standard is:

- Grade 1: 0,018 mm up to and including 2,000 mm;
- Grade 2: 0,020 mm up to and including 2,000 mm.

The nominal conductor diameters are specified in Clause 4 of IEC 60317-0-1:2013.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60317-0-1:2013, *Specifications for particular types of winding wires – Part 0-1: General requirements – Enamelled round copper wire*

3 Terms, definitions, general notes and appearance

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in 3.1 of IEC 60317-0-1:2013 apply.

3.2 General notes

3.2.1 Methods of test

Subclause 3.2 of IEC 60317-0-1:2013 applies. In case of inconsistencies between IEC 60317-0-1 and this standard, IEC 60317-4 shall prevail.

3.2.2 Winding wire

Class 130 is a thermal class that requires a minimum temperature index of 130 and a heat shock temperature of at least 155 °C.

The temperature in degrees Celsius corresponding to the temperature index is not necessarily that at which it is recommended that the wire be operated and this will depend on many factors, including the type of equipment involved.