
**Plastics — Methods of exposure to
laboratory light sources —**

**Part 3:
Fluorescent UV lamps**

*Plastiques — Méthodes d'exposition à des sources lumineuses de
laboratoire —*

Partie 3: Lampes fluorescentes UV



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	2
4.1 Laboratory light source.....	2
4.2 Test chamber.....	5
4.3 Radiometer.....	5
4.4 Black-panel/black-standard thermometer.....	5
4.5 Wetting.....	6
4.5.1 General.....	6
4.5.2 Spray and condensation system.....	6
4.6 Specimen holders.....	6
4.7 Apparatus to assess changes in properties.....	6
5 Test specimens	6
6 Test conditions	7
6.1 Radiation.....	7
6.2 Temperature.....	7
6.3 Condensation and spray cycles.....	7
6.4 Cycles with dark periods.....	7
6.5 Sets of exposure conditions.....	7
7 Procedure	8
7.1 General.....	8
7.2 Mounting the test specimens.....	8
7.3 Exposure.....	8
7.4 Measurement of radiant exposure.....	9
7.5 Determination of changes in properties after exposure.....	9
8 Exposure report	9
Annex A (informative) Relative irradiance of typical fluorescent UV lamps	10
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 6, *Ageing, chemical and environmental resistance*.

This fourth edition cancels and replaces the third edition (ISO 4892-3:2013), of which it constitutes a minor revision with the following change:

— in [A.2.3](#), further information on lamp combination is added.

ISO 4892 consists of the following parts, under the general title *Plastics — Methods of exposure to laboratory light sources*:

- *Part 1: General guidance*
- *Part 2: Xenon-arc lamps*
- *Part 3: Fluorescent UV lamps*
- *Part 4: Open-flame carbon-arc lamps*

Plastics — Methods of exposure to laboratory light sources —

Part 3: Fluorescent UV lamps

1 Scope

This part of ISO 4892 specifies methods for exposing specimens to fluorescent UV radiation, heat and water in apparatus designed to simulate the weathering effects that occur when materials are exposed in actual end-use environments to global solar radiation, or to solar radiation through window glass.

The specimens are exposed to fluorescent UV lamps under controlled environmental conditions (temperature, humidity and/or water). Different types of fluorescent UV lamp can be used to meet all the requirements for testing different materials.

Specimen preparation and evaluation of the results are covered in other International Standards for specific materials.

General guidance is given in ISO 4892-1.

NOTE Fluorescent UV lamp exposures for paints, varnishes and other coatings are described in ISO 11507.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or laboratory light sources*

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance*

3 Principle

3.1 Fluorescent UV lamps, when following the manufacturer's recommendations for lamp maintenance and/or rotation, may be used to simulate the spectral irradiance of global solar radiation in the short wavelength ultraviolet (UV) region of the spectrum.

3.2 Specimens are exposed to various levels of UV radiation, heat and moisture (see [3.4](#)) under controlled environmental conditions.

3.3 The exposure conditions may be varied by selection of the following:

- a) type of fluorescent UV lamp;
- b) irradiance level;
- c) temperature during the UV exposure;
- d) type of wetting (see [3.4](#));