

INTERNATIONAL  
STANDARD

ISO  
19403-1

First edition  
2017-06

---

---

**Paints and varnishes — Wettability —**  
**Part 1:**  
**Terminology and general principles**

*Peintures et vernis — Mouillabilité —*

*Partie 1: Terminologie et principes généraux*



Reference number  
ISO 19403-1:2017(E)

© ISO 2017



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
3.1 Determination of the surface free energy.....	1
3.2 Determination of the surface tension of liquids.....	3
<b>4 General principles</b> .....	<b>5</b>
4.1 Principles for the determination of the surface free energy.....	5
4.2 Principles for the measurement of the surface tension at the pendant drop.....	6
<b>Bibliography</b> .....	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

A list of all parts in the ISO 19403 series can be found on the ISO website.

# Paints and varnishes — Wettability —

## Part 1: Terminology and general principles

### 1 Scope

The ISO 19403 series specifies optical test methods

- for the measurement of the contact angle,
- for the determination of the free surface energy of a solid surface, including the polar and dispersive fractions,
- for the determination of the surface tension of liquids, including the polar and dispersive fractions, and
- for the checking of the measurement arrangement with reference materials.

It can be applied for the characterization of substrates, coatings and coating materials.

The applicability can be restricted for liquids with non-Newtonian rheology<sup>1)</sup>.

This document specifies terms and definitions and defines the general principles.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4618, *Paints and varnishes — Terms and definitions*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

#### 3.1 Determination of the surface free energy

##### 3.1.1

##### **chemical homogeneity**

chemically homogeneous composition of a surface to be examined

Note 1 to entry: The definition regards a purely qualitative assessment of the surface. Regarding the measurement of the contact angle, a surface is considered chemically and topologically sufficiently homogeneous if no significant differences of the contact angles can be determined when measuring on several areas on the surface. The significance limits can be specified by the user in accordance with standard laboratory methods.

1) This term is defined in DIN 1342-1.