
Rubber, raw — Determination of bound acrylonitrile content in acrylonitrile-butadiene rubber (NBR) —

**Part 2:
Kjeldahl method**

Caoutchouc brut — Détermination du contenu en acrylonitrile lié dans le caoutchouc acrylonitrile-butadiène (NBR) —

Partie 2: Méthode Kjeldahl





COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents and materials	2
6 Apparatus	2
7 Sampling, preparation of the sample for the determination and preparation of reagents ...	3
7.1 Raw NBR, XNBR or NBIR rubber.....	3
7.2 NBR Latex.....	3
7.3 Preparation of reagents.....	4
8 Procedure	4
9 Calculation of bound acrylonitrile content	5
9.1 When sulfuric acid (0,05 mol/dm ³) is used as the standard volumetric solution.....	5
9.2 When hydrochloric acid (0,05 mol/dm ³) is used as the standard volumetric solution.....	5
10 Precision	5
11 Test report	6
Annex A (informative) Examples of automatic analysers based on the Kjeldahl method	7
Annex B (informative) Precision on NBR	9
Annex C (informative) Precision on NBR Latex	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This second edition cancels and replaces the first edition (ISO 24698-2:2008), which has been technically revised.

The main changes compared to the previous edition are as follows:

- addition in the scope of two types of raw rubbers, XNBR and NBIR, that contain acrylonitrile;
- addition of NBR latex to the scope and in sample preparation ([7.2](#));
- amendment of finishing condition of sample weight in [7.1](#);
- addition of ITP results of NBR latex in a new [Annex C](#).

A list of all the parts in the ISO 24698 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Rubber, raw — Determination of bound acrylonitrile content in acrylonitrile-butadiene rubber (NBR) —

Part 2: Kjeldahl method

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices.

CAUTION — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document specifies a method for the determination of the bound acrylonitrile content in NBR by an automatic analyser which uses the Kjeldahl method. The method is also applicable to XNBR (carboxylic acrylonitrile-butadiene rubber) and NBIR (acrylonitrile-butadiene-isoprene rubber) as well as NBR latex.

NOTE This document and ISO 24698-1 can give different results on the same rubber sample.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 123, *Rubber latex — Sampling*

ISO 1407:2011, *Rubber — Determination of solvent extract*

ISO 1795, *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

The nitrogen in a sample of raw rubber is converted into an ammonium salt by digestion with potassium sulfate, sulfuric acid and a copper sulfate catalyst. Ammonia is then released by the addition of strong alkali and steam-distilled into boric acid solution and titrated with standard volumetric acid solution.