
**Rubber, vulcanized or
thermoplastic — Determination
of stress in tension under non-
isothermal conditions**

*Caoutchouc vulcanisé ou thermoplastique — Détermination de la
contrainte en traction dans des conditions non isothermes*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
5.1 Test machine.....	2
5.1.1 General.....	2
5.1.2 Thermal-stress testing machine.....	2
5.1.3 Stress relaxometer.....	3
5.2 Oven.....	4
5.3 Thickness- and width-measuring devices.....	4
6 Calibration	4
7 Test piece	4
7.1 Dimensions.....	4
7.1.1 Method A:.....	4
7.1.2 Method B:.....	4
7.2 Number of test pieces.....	5
7.3 Time lapse between moulding and testing.....	5
7.4 Conditioning.....	5
8 Test conditions	5
8.1 Heating rate and temperature interval under investigation.....	5
8.2 Strain of the sample.....	5
9 Procedure	6
9.1 Method A.....	6
9.2 Method B.....	7
9.2.1 Isothermal test period.....	7
9.2.2 Non-isothermal test period (TSSR, temperature scanning stress relaxation test).....	7
10 Evaluation of the data and expression of results	8
10.1 Method A.....	8
10.2 Method B.....	9
11 Precision	13
12 Test report	13
12.1 Test report Method A.....	13
12.2 Test report Method B.....	14
Annex A (normative) Calibration schedule	15
Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This third edition cancels and replaces the second edition (ISO 12493:2017), which has been technically revised.

The main changes are as follows:

- another method (method B) for measuring tensile stress under non-isothermal conditions has been added. In this method, the change of stress is measured at a given strain and under variation of temperature at a given heating rate as a function of temperature.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Usually, stress relaxation tests (see ISO 6914) are performed at constant temperature conditions because temperature has a strong impact on the relaxation time constants of rubber materials. Depending on the respective relaxation time constant or, more realistic, relaxation time spectrum, those measurements are more or less time consuming and can require testing times of several days, weeks or even months. Accelerated stress relaxation tests can be performed under non-isothermal conditions, if the temperature is increased at a certain constant heating rate, because relaxation processes are thermally activated and therefore occur faster at higher temperatures. Thus, the entire stress relaxation behaviour of the material can be scanned within a short period of time, typically a few hours. This method is designated as the temperature scanning stress relaxation (TSSR) test method and offers the ability to characterize rubber – vulcanized or thermoplastic – by short-term measurements. TSSR tests cannot replace conventional isothermal stress relaxation measurements, but are considered as a comparative test method, e.g. for the purpose of material pre-selection or in order to determine the state of crosslink density – which is an important reason for ageing phenomena – of a sample.

During non-isothermal testing, the material undergoes not only stress relaxation, but additional phenomena occur which need to be considered by adequate corrections. Most important in this case is an increase of retractive forces due to the Gough-Joule effect and thermal expansion of the sample. Whereas the latter can be numerically compensated by considering a proper value of the coefficient of thermal expansion (CTE), the increase of retractive forces offer the opportunity to calculate the crosslink density of the material, based on fundamental theory of rubber elasticity. Furthermore, an enhanced sensitivity of the test, with respect to specific relaxation processes is achieved by determination of the first derivative of the measured stress-temperature curve. Similar to stress relaxation measurements in the time domain, the latter can be used to calculate a corresponding relaxation temperature spectrum, instead of a relaxation time spectrum.

Rubber, vulcanized or thermoplastic — Determination of stress in tension under non-isothermal conditions

WARNING 1 — Users of this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of users to establish appropriate safety and health practices and determine the applicability of any other restrictions.

WARNING 2 — Certain procedures specified in this document can involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document describes two methods for measuring stress in tension under non-isothermal conditions.

- Method A: The thermal stress is measured for various pre-strain and temperature conditions as a function of time.
- Method B: The change of stress is measured in a test piece at a given strain and under variation of temperature at a given heating rate as a function of temperature. In this way, the determination of the thermal-mechanical behaviour of a rubber can be accelerated, e.g. for the purpose of comparative testing of aging or estimating the upper limit of the operating temperature.

The measurement device, which is equipped with a suitable heating chamber, is used to record the stress as a function of time or temperature until the sample breaks or the stress has approached zero or for a certain time.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 188:2011, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 5893, *Rubber and plastics test equipment — Tensile, flexural and compression types (constant rate of traverse) — Specification*

ISO 18899:2013, *Rubber — Guide to the calibration of test equipment*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>