
**Metallic coatings — Hot dip galvanized
coatings on ferrous materials —
Gravimetric determination of the
mass per unit area**

*Revêtements métalliques — Revêtements de galvanisation à chaud
sur métaux ferreux — Détermination gravimétrique de la masse par
unité de surface*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Stripping solution	1
6 Sampling	1
7 Procedure	1
8 Expression of results	2
8.1 Method of calculation	2
8.2 Reproducibility	2
9 Test report	2

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, Subcommittee SC 4, *Hot dip coatings (galvanized, etc.)*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 262, *Metallic and other inorganic coatings, including for corrosion protection and corrosion testing of metals and alloys*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 1460:1992), which has been technically revised. The main changes compared with the previous edition are as follows:

- the density of concentrated hydrochloric acid in [Clause 5](#) has been modified from $\rho = 1,19$ g/ml to $\rho \geq 1,18$ g/ml.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Metallic coatings — Hot dip galvanized coatings on ferrous materials — Gravimetric determination of the mass per unit area

1 Scope

This document specifies a method of determining the mass per unit area of hot dip galvanized coatings on ferrous materials.

Since an exact knowledge of the area of the surface is essential, this document is mainly applicable to shapes whose areas are easy to determine. If, with heavy samples, the specifications of [Clause 7](#) cannot be met, then the hot dip galvanized coating mass is determined by another method.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

The hot dip galvanized coating on a surface of known area is dissolved in inhibited acid and the resultant loss in mass is determined by weighing the sample before and after the coating is dissolved.

5 Stripping solution

Dissolve 3,5 g of hexamethylenetetramine in 500 ml of concentrated hydrochloric acid ($\rho \geq 1,18$ g/ml). Dilute this solution to 1 000 ml with distilled water.

6 Sampling

The method of sampling shall be agreed between the interested parties.

7 Procedure

Where necessary, the sample shall be degreased with an organic solvent that does not attack the hot dip galvanized coating and then dried.

Before stripping, the sample shall be weighed to an accuracy better than 1 % of the presumed coating mass.

The quantity of solution shall be measured so that at least 10 ml of solution are available for each square centimetre of the surface of the sample. The sample shall be completely immersed in the solution