

Steels for Hydrogen Service at Elevated Temperatures and Pressures in Petroleum Refineries and Petrochemical Plants

API RECOMMENDED PRACTICE 941
SEVENTH EDITION, AUGUST 2008



Steels for Hydrogen Service at Elevated Temperatures and Pressures in Petroleum Refineries and Petrochemical Plants

Downstream Segment

API RECOMMENDED PRACTICE 941
SEVENTH EDITION, AUGUST 2008



Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

Classified areas may vary depending on the location, conditions, equipment, and substances involved in any given situation. Users of this recommended practice should consult with the appropriate authorities having jurisdiction.

Users of this recommended practice should not rely exclusively on the information contained in this document. Sound business, scientific, engineering, and safety judgement should be used in employing the information contained herein.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

All rights reserved. No part of this work may be reproduced, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, N.W., Washington, D.C. 20005.

Copyright © 2008 American Petroleum Institute

Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, N.W., Washington, D.C. 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually and updated quarterly by API, 1220 L Street, N.W., Washington, D.C. 20005.

Suggested revisions are invited and should be submitted to the Standards Department, API, 1220 L Street, NW, Washington, D.C. 20005, standards@api.org.

Contents

	Page
1	Scope 1
2	References 1
2.1	Standards 1
3	Operating Limits 2
3.1	Basis for Setting Operating Limits 2
3.2	Selecting Materials for New Equipment 2
3.3	High Temperature Hydrogen Attack (HTHA) in a Liquid Hydrocarbon Phase 2
3.4	References and Comments for Figure 1. 4
4	Forms of HTHA 6
4.1	General 6
4.2	Surface Decarburization 6
4.3	Internal Decarburization and Fissuring 7
5	Factors Influencing HTHA 7
5.1	Incubation Time 7
5.2	Effect of Primary Stresses 9
5.3	Effect of Secondary Stresses 9
5.4	Effect of Heat Treatment 9
5.5	Effect of Stainless Steel Cladding or Weld Overlay 10
6	Inspection for HTHA 11
	Annex A High Temperature Hydrogen Attack (HTHA) of 0.5Mo Steels 15
	Annex B HTHA of 1.25 Cr-0.5Mo Steel 25
	Annex C HTHA of 2.25Cr-1Mo Steel 27
	Annex D Effective Pressures of Hydrogen in Steel Covered by Clad/Overlay 29
	Annex E Summary of Inspection Methods 31
	Annex F Request for New Information 37
	Bibliography 39
Figures	
1	Operating Limits for Steels in Hydrogen Service to Avoid Decarburization and Fissuring 3
2	C-0.5Mo Steel (ASTM A204-A) Showing Internal Decarburization and Fissuring in High Temperature Hydrogen Service 8
3	Time for Incipient Attack of Carbon Steel in High Temperature Hydrogen Service 12
A.1	Experience with C-0.5Mo and Mn-0.5Mo Steel in High Temperature Hydrogen Service 17
A.2	Steels in High Temperature Hydrogen Service Showing Effect of Molybdenum and Trace Alloying Elements 22
A.3	Time for Incipient Attack of 0.5Mo Steels in High Temperature Hydrogen Service 24
B.1	Operating Conditions for 1.25Cr-0.5Mo Steels That Experienced HTHA Below the Figure A.1 Curve 26
C.1	Operating Conditions of 2.25Cr-1Mo Steels That Experienced HTHA Below the Figure A.1 Curve 28
Tables	
A.1	Operating Conditions for C-0.5Mo Steels That Experienced High Temperature Hydrogen Attack Below the 0.5Mo Steel Curve in Figure A.1 21
B.1	Experience with HTHA of 1.25Cr-0.5Mo Steel at Operating Conditions Below the Figure A.1 Curve 25

C.1 Experience with HTHA of 2.25Cr-1Mo Steel at Operating Conditions Below the Figure A.1 Curve	27
E.1 Summary of Inspection Methods for HTHA	32
E.2 Summary of Ultrasonic Inspection Methods for HTHA.	35

Introduction

At normal atmospheric temperatures, gaseous molecular hydrogen does not readily permeate steel, even at high pressures. Carbon steel is the standard material for cylinders that are used to transport hydrogen at pressures of 2000 psi (14 MPa). Many postweld heat treated carbon steel pressure vessels have been used successfully in continuous service at pressures up to 10,000 psi (69 MPa) and temperatures up to 430°F (221°C). However, under these same conditions, highly stressed carbon steels and hardened steels have cracked due to hydrogen embrittlement.

The recommended maximum hydrogen partial pressure at atmospheric temperature for carbon steel fabricated in accordance with the ASME *Boiler and Pressure Vessel Code* is 13,000 psia (90 MPa). Below this pressure, carbon steel equipment has shown satisfactory performance. Above this pressure, very little operating and experimental data are available. If plants are to operate at hydrogen partial pressures that exceed 13,000 psia (90 MPa), the use of an austenitic stainless steel liner with venting in the shell should be considered.

At elevated temperatures, molecular hydrogen dissociates into the atomic form, which can readily enter and diffuse through the steel. Under these conditions, the diffusion of hydrogen in steel is more rapid. As discussed in Section 4, hydrogen reacts with the carbon in the steel to cause either surface decarburization or internal decarburization and fissuring, and eventually cracking. This form of hydrogen damage is called high temperature hydrogen attack (HTHA) and this recommended practice discusses the resistance of steels to HTHA.

Steels for Hydrogen Service at Elevated Temperatures and Pressures in Petroleum Refineries and Petrochemical Plants

1 Scope

This recommended practice (RP) summarizes the results of experimental tests and actual data acquired from operating plants to establish practical operating limits for carbon and low alloy steels in hydrogen service at elevated temperatures and pressures. The effects on the resistance of steels to hydrogen at elevated temperature and pressure that result from high stress, heat treating, chemical composition, and cladding are discussed. This RP does not address the resistance of steels to hydrogen at lower temperatures [below about 400°F (204°C)], where atomic hydrogen enters the steel as a result of an electrochemical mechanism.

This RP applies to equipment in refineries, petrochemical facilities, and chemical facilities in which hydrogen or hydrogen-containing fluids are processed at elevated temperature and pressure. The guidelines in this RP can also be applied to hydrogenation plants such as those that manufacture ammonia, methanol, edible oils, and higher alcohols.

Hydrogenation processes usually require standards and materials that may not be warranted in other operations of the petroleum industry. At certain combinations of elevated temperature and hydrogen partial pressure, both chemical and metallurgical changes occur in carbon steel, which in advanced stages can render it unsuitable for safe operation. Alloy steels containing chromium and molybdenum can be used under such conditions.

The steels discussed in this RP resist high temperature hydrogen attack (HTHA) when operated within the guidelines given. However, they may not be resistant to other corrosives present in a process stream or to other metallurgical damage mechanisms operating in the HTHA range. This RP also does not address the issues surrounding possible damage from rapid cooling of the metal after it has been in high temperature, high pressure hydrogen service (e.g. possible need for outgassing hydroprocessing reactors). This RP will discuss in detail only the resistance of steels to HTHA.

Presented in this document are curves that indicate the operating limits of temperature and hydrogen partial pressure for satisfactory performance of carbon steel and Cr-Mo steels in elevated temperature, hydrogen service. In addition, it includes a summary of inspection methods to evaluate equipment for the existence of HTHA.

2 References

2.1 Standards

Unless otherwise specified, the most recent editions or revisions of the following codes shall, to the extent specified herein, form a part of this publication.

ASME *Boiler and Pressure Vessel Code, Section II*¹—*Materials—Part A: Ferrous Material Specifications, and Part D: Properties, Section III—Rules for Construction of Nuclear Power Plant Components, and Section VIII—Pressure Vessels, Divisions 1 and 2*

ASME *Code for Pressure Piping, ASME/ANSI B31.3—Chemical Plant and Petroleum Refinery Piping*

¹ ASME International, 3 Park Avenue, New York, New York 10016, www.asme.org.