
**Rubber — Determination of residual
unsaturation of hydrogenated nitrile
butadiene rubber (HNBR) by infrared
spectroscopy**

*Caoutchouc — Détermination de la non-saturation résiduelle du
caoutchouc nitrile butadiène hydrogéné (HNBR) par spectroscopie à
infrarouge*



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reagents	1
5 Sampling	2
6 Apparatus	2
7 Procedure	2
7.1 Sample preparation	2
7.1.1 Purification by precipitation	2
7.1.2 Purification by extraction.....	2
7.1.3 Preparation of cast HNBR film.....	3
7.2 Obtaining the IR spectrum.....	3
8 Calculations	3
9 Precision	4
10 Test report	4
Annex A (informative) Example of infrared spectrum interpretation and calculation	5
Annex B (informative) Precision	6
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#).

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This second edition cancels and replaces the first edition (ISO 14558:2000), of which it constitutes a minor revision where the normative references were updated and the precision data were moved to an informative [Annex B](#).

Rubber — Determination of residual unsaturation of hydrogenated nitrile butadiene rubber (HNBR) by infrared spectroscopy

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies a method for determining the residual unsaturation in hydrogenated nitrile rubber (HNBR) by measuring the infrared (IR) absorbance of HNBR films cast from solution.

This International Standard assumes that samples and IR spectra are prepared and analysed by experienced personnel and that equipment is operated in accordance with the manufacturer's instructions. Details for operating an IR spectrometer are not included in this method.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1795, *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

3 Principle

Raw, unvulcanized HNBR is purified by precipitation with methanol from a solution in methyl ethyl ketone (MEK) or by extraction of the solid HNBR with methanol in a Soxhlet apparatus.

The purified sample is dissolved in MEK and a film is cast on a potassium bromide (KBr) disc.

The IR spectrum of the film is obtained with a Fourier-transform (FT) or dispersive IR spectrometer.

The “corrected absorbance” of the specific absorbance bands for acrylonitrile (AN), butadiene (BD) and hydrogenated butadiene (HBD) are determined using the baseline method and the percentage of residual unsaturation (double bonds in unhydrogenated butadiene) is calculated with the aid of absorbance factors from the literature (see [8.5](#)).

4 Reagents

Reagent grade chemicals should preferably be used in all determinations. Other grades may be used provided that they are of sufficiently high purity not to lessen the accuracy of the determination.

4.1 Methyl ethyl ketone (MEK).

4.2 Methanol.

4.3 Dry, compressed nitrogen.