
**Rubber, raw — Determination
of block polystyrene content —
Ozonolysis method**

*Caoutchouc brut — Dosage du polystyrène séquencé — Méthode de
l'ozonolyse*



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Reactions	1
5 Reagents	2
6 Apparatus	2
7 Sample preparation	2
7.1 General	2
7.2 Latex	3
7.3 Oil-extended solid rubber	3
8 Procedure	3
9 Expression of results	4
10 Test report	4
Bibliography	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This third edition cancels and replaces the second edition (ISO 6235:1995), of which it constitutes a minor revision with the following changes.

- the Normative References have been updated;
- in [7.2](#), the text in ISO 4655:1985, 4.4 has been included, because this International Standard has been withdrawn;
- a Bibliography has been added.

Rubber, raw — Determination of block polystyrene content — Ozonolysis method

WARNING — Persons using this International Standard should be familiar with normal laboratory practice. This International Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

1 Scope

This International Standard specifies a method for the determination of the long polystyrene block content of raw uncompounded styrene-butadiene rubber (SBR) and raw uncompounded blends of block SBR.

It is not applicable to blends of block SBR with EPDM, IIR, CSM and other halogenated rubbers.

The method is applicable to raw, uncompounded latices of the above compositions and is suitable for rubbers having block polystyrene contents in the range from 5 % (by weight) to 100 % (by weight).

Rubbers having block polystyrene contents of less than 5 % (by weight) may yield incorrect results unless a correction factor, based on information gained by working with such rubbers, is applied.

The method is intended for use on gel-free rubbers, but it may be used on rubbers containing gel if it has been proved that the gel does not interfere.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1407, *Rubber — Determination of solvent extract*

ISO 4793, *Laboratory sintered (fritted) filters — Porosity grading, classification and designation*

3 Principle

A test portion is dissolved in dichloromethane and the ethylenic bonds in the rubber ruptured by reaction with ozone. The ozonides thus formed are subsequently decomposed by methanolic sulfuric acid solution.

4 Reactions

The reactions upon which the method is based are as follows.

- a) Long, saturated, polystyrene blocks are not attacked by ozone, but small fragments (aldehydes and carboxylic acids) produced by the ozonolysis and the relatively low molecular mass polystyrene fragments from scission within the random copolymer blocks are soluble in methanolic sulfuric acid solution.
- b) Relatively high molecular mass polystyrene blocks are insoluble in methanolic sulfuric acid solution.