
**Metallic materials — Unified method
of test for the determination of
quasistatic fracture toughness**

*Matériaux métalliques — Méthode unifiée d'essai pour la
détermination de la ténacité quasi statique*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	2
5 General requirements	5
5.1 General	5
5.2 Fracture parameters	7
5.3 Fracture toughness symbols	8
5.4 Test specimens	8
5.4.1 Specimen configuration and size	8
5.4.2 Specimen preparation	13
5.5 Pre-test requirements	19
5.5.1 Pre-test measurements	19
5.5.2 Crack shape/length requirements	19
5.6 Test apparatus	19
5.6.1 Calibration	19
5.6.2 Force application	20
5.6.3 Displacement measurement	20
5.6.4 Test fixtures	20
5.7 Test requirements	24
5.7.1 Three-point bend testing	24
5.7.2 Compact tension testing	24
5.7.3 Specimen test temperature	24
5.7.4 Recording	25
5.7.5 Testing rates	25
5.7.6 Test analyses	25
5.8 Post-test crack measurements	25
5.8.1 General	25
5.8.2 Initial crack length, a_0	25
5.8.3 Stable crack extension, Δa	30
5.8.4 Unstable crack extension	30
6 Determination of fracture toughness for stable and unstable crack extension	31
6.1 General	31
6.2 Determination of plane strain fracture toughness, K_{Ic}	32
6.2.1 General	32
6.2.2 Interpretation of the test record for F_Q	32
6.2.3 Calculation of K_Q	33
6.2.4 Qualification of K_Q as K_{Ic}	34
6.3 Determination of fracture toughness in terms of δ	34
6.3.1 Determination of F_c and V_c , F_u and V_u , or F_{uc} and V_{uc}	34
6.3.2 Determination of F_m and V_m	35
6.3.3 Determination of V_p	36
6.3.4 Calculation of δ_0	36
6.3.5 Qualification of δ_0 fracture toughness value	37
6.4 Determination of fracture toughness in terms of J	38
6.4.1 Determination of F_c and V_c or q_c , F_u and V_u or q_u , or F_{uc} and V_{uc} or q_{uc}	38
6.4.2 Determination of F_m and q_m	38
6.4.3 Determination of U_p	38
6.4.4 Calculation of J_0	39
6.4.5 Qualification of J_0 fracture toughness value	40

7	Determination of resistance curves δ-Δa and J-Δa and initiation toughness $\delta_{0,2BL}$ and $J_{0,2BL}$ and δ_i and J_i for stable crack extension	41
7.1	General	41
7.2	Test procedure	41
7.2.1	General	41
7.2.2	Multiple-specimen procedure	41
7.2.3	Single-specimen procedure	41
7.2.4	Final crack front straightness	42
7.3	Calculation of J and δ	42
7.3.1	Calculation of J	42
7.3.2	Calculation of δ	42
7.4	R-curve plot	43
7.4.1	Plot construction	44
7.4.2	Data spacing and curve fitting	45
7.5	Qualification of resistance curves	46
7.5.1	Qualification of J - Δa resistance curves	46
7.5.2	Qualification of δ - Δa resistance curves	46
7.6	Determination and qualification of $J_{0,2BL}$ and $\delta_{0,2BL}$	47
7.6.1	Determination of $J_{0,2BL}$	47
7.6.2	Determination of $\delta_{0,2BL}$	48
7.7	Determination of initiation toughness J_i and δ_i by scanning electron microscopy (SEM)	49
8	Test report	49
8.1	Organization	49
8.2	Specimen, material and test environment	50
8.2.1	Specimen description	50
8.2.2	Specimen dimensions	50
8.2.3	Material description	50
8.2.4	Additional dimensions	50
8.2.5	Test environment	50
8.2.6	Fatigue precracking conditions	50
8.3	Test data qualification	51
8.3.1	Limitations	51
8.3.2	Crack length measurements	51
8.3.3	Fracture surface appearance	51
8.3.4	Pop-in	51
8.3.5	Resistance curves	51
8.3.6	Checklist for data qualification	51
8.4	Qualification of K_{Ic}	52
8.5	Qualification of $\delta_{c(B)}$, $\delta_{u(B)}$, $\delta_{uc(B)}$ or $\delta_{m(B)}$	52
8.6	Qualification of $J_{c(B)}$, $J_{u(B)}$, $J_{uc(B)}$ or $J_{m(B)}$	53
8.7	Qualification of the δ - R Curve	53
8.8	Qualification of the J - R Curve	53
8.9	Qualification of $\delta_{0,2BL(B)}$ as $\delta_{0,2BL}$	53
8.10	Qualification of $J_{0,2BL(B)}$ as $J_{0,2BL}$	53
	Annex A (informative) Determination of δ_i and J_i	55
	Annex B (normative) Crack plane orientation	60
	Annex C (informative) Example test reports	62
	Annex D (informative) Stress intensity factor coefficients and compliance relationships	71
	Annex E (informative) Measurement of load-line displacement q in the three-point bend test	75
	Annex F (informative) Derivation of pop-in formulae	80
	Annex G (informative) Analytical methods for the determination of V_p and U_p	82
	Annex H (informative) Guidelines for single-specimen methods	83
	Annex I (normative) Power-law fits to crack extension data (see Reference [42])	97

Bibliography 98

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 4, *Fatigue, fracture and toughness testing*.

This third edition cancels and replaces the second edition (ISO 12135:2016), which has been technically revised.

The main changes compared to the previous edition are as follows:

- formulae to calculate CTOD have been replaced with those based on rigid rotation assumption throughout; replacing the previous *R*-curve formulae based on CTOD from *J*. CTOD formulae for SENBs are now those based on recent research to include the material yield to tensile strength ratio in the CTOD formulae;
- the determination of *J* directly from displacement defined in terms of CMOD has been included, in addition to the methods based on load line displacement;
- where fatigue precrack straightness requirements cannot be met due to internal residual stresses, the application of modification techniques, originally developed for weld specimens, is now permitted;
- the rotation correction factor for compact specimens has been revised with a new formula;
- editorial changes have been made to improve consistency of terms and definitions used throughout the document.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Metallic materials — Unified method of test for the determination of quasistatic fracture toughness

1 Scope

This document specifies methods for determining fracture toughness in terms of K , δ , J and R -curves for homogeneous metallic materials subjected to quasistatic loading. Specimens are notched, precracked by fatigue and tested under slowly increasing displacement. The fracture toughness is determined for individual specimens at or after the onset of ductile crack extension or at the onset of ductile crack instability or unstable crack extension. In cases where cracks grow in a stable manner under ductile tearing conditions, a resistance curve describing fracture toughness as a function of crack extension is measured. In some cases in the testing of ferritic materials, unstable crack extension can occur by cleavage or ductile crack initiation and growth, interrupted by cleavage extension. The fracture toughness at crack arrest is not covered by this document. Special testing requirements and analysis procedures are necessary when testing weldments, and these are described in ISO 15653 which is complementary to this document.

Statistical variability of the results strongly depends on the fracture type, for instance, fracture toughness associated with cleavage fracture in ferritic steels can show large variation. For applications that require high reliability, a statistical approach can be used to quantify the variability in fracture toughness in the ductile-to-brittle transition region, such as that given in ASTM E1921. However, it is not the purpose of this document to specify the number of tests to be carried out nor how the results of the tests are to be applied or interpreted.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3785, *Metallic materials — Designation of test specimen axes in relation to product texture*

ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system*

ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 stress intensity factor

K
magnitude of the elastic stress-field singularity for a homogeneous, linear-elastic body

Note 1 to entry: The stress intensity factor is a function of applied force, crack length, specimen size and specimen geometry.