

---

---

**Rubber compounding ingredients —  
Carbon black — Determination of  
sulfur content**

*Ingrédients de mélange du caoutchouc — Noir de carbone — Dosage  
du soufre total*





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Method A: Combustion furnace.....</b>	<b>1</b>
4.1 Principle.....	1
4.2 Reagents.....	1
4.3 Apparatus.....	2
4.4 Procedure.....	2
4.5 Expression of results.....	3
4.6 Test report.....	3
<b>5 Method B: Automatic analyser.....</b>	<b>3</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This third edition cancels and replaces ISO 1138:2007 and ISO 1138:2007/Amd 1:2012, which have been technically revised.

The main changes are as follows:

- withdrawal of the method using an oxygen bomb calorimeter (previously called Method A) due to the use of hazardous chemicals, and withdrawal of Amendment 1:2012 related to that method;
- addition of CAS numbers to the chemical reagents used in the current Method A.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Rubber compounding ingredients — Carbon black — Determination of sulfur content

## 1 Scope

This document specifies two methods for the determination of the total sulfur in all types of carbon black for use in the rubber industry:

- Method A, using a combustion furnace;
- Method B, using an automatic analyser.

With respect to safety aspects and test precision, it is preferable to use automatic systems. Method B is therefore the preferred method. Classical chemical analysis (Method A) is acceptable if automatic equipment is not available.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 15671, *Rubber and rubber additives — Determination of total sulfur content using an automatic analyser*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

## 4 Method A: Combustion furnace

### 4.1 Principle

A weighed test portion of dried carbon black is heated at a temperature of 1 425 °C in a combustion furnace in a stream of oxygen. The sulfur compounds evolved from the test portion are collected in a titrating flask containing hydrochloric acid solution. These compounds are titrated with standard volumetric potassium iodate-potassium iodide solution. The percentage of sulfur is calculated.

### 4.2 Reagents

During the analysis, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

#### 4.2.1 Hydrochloric acid.

Mix 2 volumes of concentrated hydrochloric acid ( $\rho_{20}$  1,19 g/ml; CAS 7647-01-0) with 13 volumes of water; CAS 7732-18-5.