

ANSI/AWWA **C602-23**
(Revision of ANSI/AWWA C602-17)

AWWA Standard

Cement–Mortar Lining of Water Pipelines in Place—4 In. (100 mm) and Larger

Effective date: June 1, 2023.

First edition approved by Board of Directors June 17, 1955.

This edition approved Jan. 12, 2023.

Approved by American National Standards Institute Jan. 12, 2023.


AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or codes of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed in the Official Notice section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of publication. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; 212.642.4900; or emailing info@ansi.org.



ISBN-13, print: 978-1-64717-127-8

ISBN-13, electronic: 978-1-61300-658-0

DOI: <http://dx.doi.org/10.12999/AWWA.C602.23>

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher. Please send any requests or questions to permissions@awwa.org.

Copyright © 2023 by American Water Works Association
Printed in USA

Committee Personnel

The Steel Water Pipe Manufacturers Technical Advisory Committee (SWPMTAC) Task Group for C602, which revised this standard, had the following personnel at the time:

Christopher Walsh, *Chair*

Bruce J. Britton, *Vice-Chair*

H.H. Bardakjian, Manufacturers Consultant, Glendale, Calif.

B.J. Britton, W. Walsh Company, Attleboro, Mass.

R.J. Card, Manufacturers Consultant, Sugar Hill, Ga.

D.W. Dunker, Thompson Pipe Group, Grand Prairie, Tex.

D.P. Ebner, Michaels Corporation, Watertown, Conn.

B.D. Keil, Northwest Pipe Company, Salt Lake City, Utah

J.L. Luka, American SpiralWeld Pipe Company, Columbia, S.C.

C.J. Walsh, W. Walsh Company, Attleboro, Mass.

The AWWA Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

John H. Bambei Jr., *Chair*

Bob J. Card, *Vice-Chair*

John L. Luka, *Secretary*

General Interest Members

S.A. Arnaout (*alternate*), Stantec, Dallas, Tex.

J.H. Bambei Jr., Bambei Engineering Services, Arvada, Colo.

R.J. Card, Lockwood, Andrews & Newnam Inc., Houston, Tex.

R.L. Gibson, Freese and Nichols Inc., Fort Worth, Tex.

M.D. Gossett, HDR, Denver, Colo.

M.B. Horsley (*alternate*), Horsley Engineering LLC, Overland Park, Kans.

R. Issa, AECOM, McKinney, Tex.

C.H. Kirby (*alternate*), Lockwood, Andrews & Newnam Inc., Houston, Tex.

R.A. Kufaas, Norske Corrosion & Inspection Services Ltd., Abbotsford, B.C., Canada

D.L. McPherson (*alternate*), HDR, Charlotte, N.C.

A. Murdock, Jacobs, Salt Lake City, Utah

R. Ortega, Aurora Technical Services, Houston, Tex.

E.S. Ralph (*liaison, nonvoting*), Standards Engineer Liaison, AWWA, Denver, Colo.
A.E. Romer (*alternate*), AECOM, Orange, Calif.
J.R. Snow, Stantec, Denver, Colo.
A.M. Stanton, Black & Veatch, Pasadena, Calif.
W.R. Whidden, Woolpert, Winter Park, Fla.

Producer Members

H.H. Bardakjian, Consultant, Glendale, Calif.
D. Dechant, Dechant Infrastructure Service, Aurora, Colo.
D.W. Dunker, Thompson Pipe Group, Rialto, Calif.
B.D. Keil, Northwest Pipe Company, Salt Lake City, Utah
J.L. Luka, American SpiralWeld Pipe Company, Columbia, S.C.
R.D. Mielke (*alternate*), Northwest Pipe Company, Raleigh, N.C.
G.F. Ruchti (*alternate*), Consultant, Punta Gorda, Fla.
B.P. Simpson (*alternate*), American Cast Iron Pipe Company, Birmingham, Ala.
C.C. Sundberg, Victaulic, Issaquah, Wash.
R. Wu, (*alternate*), Thompson Pipe Group, Grand Prairie, Tex.

User Members

L. Adams, US Bureau of Reclamation, Denver, Colo.
G.A. Andersen, New York City Bureau of Water Supply, Little Neck, N.Y.
B. Cheng, Metro Vancouver, Burnaby, B.C., Canada
B. Fountain, San Diego County Water Authority, San Diego, Calif.
J. Fox, Tampa Bay Water, Clearwater, Fla.
J. Garcia (*alternate*), Metropolitan Water District, La Verne, Calif.
S. Hattan, Tarrant Regional Water District, Fort Worth, Tex.
M. Lobik, Springfield Water & Sewer, Springfield, Mass.
T. Peng, Metropolitan Water District, Los Angeles, Calif.
G. Ramon (*liaison, nonvoting*), Standards Council Liaison, Little Rock Water Reclamation Authority, Little Rock, Ark.
V. Scutelnicu, Los Angeles Department of Water and Power, Los Angeles, Calif.
M. Turney (*alternate*), Denver Water, Denver, Colo.

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
Foreword		4.7	Contingent Work 11
I	Introduction..... vii	4.8	Methods for Lining of New Steel Pipe..... 11
I.A	Background..... vii	5	Verification
I.B	History..... vii	5.1	Inspection 14
I.C	Acceptance viii	5.2	Inspection of Rehabilitated Pipelines..... 15
II	Special Issues ix	5.3	Inspection of New Steel Pipe 16
III	Use of This Standard ix	6	Delivery
III.A	Purchaser Options and Alternatives ix	6.1	Marking 18
III.B	Modification to Standard xi	6.2	Shipping..... 18
IV	Major Revisions..... xi	6.3	Affidavit of Compliance 18
V	Comments xi	Figures	
Standard		1	Nominal Slumps of Cement– Mortar Mixes for Application of Pipe Linings Using Pump Feed 5
1	General	2	Slump Limits of Cement Mortar for Application of Pipe Linings Using Mechanical Feed 5
1.1	Scope 1	Tables	
1.2	Purpose 1	1	Recommended Thickness of Cement–Mortar Lining for Pipelines in Place 6
1.3	Application..... 2	2	Acceptable Performance for Smooth-Bore Pipe..... 16
2	References 2		
3	Definitions 2		
4	Requirements		
4.1	Workmanship..... 3		
4.2	Equipment 3		
4.3	Materials for Construction 3		
4.4	General Cement–Mortar Lining Design..... 4		
4.5	Methods for Construction of Rehabilitated Pipelines 6		
4.6	Temporary Bypass to Customers..... 10		

This page intentionally blank.

Foreword

This foreword is for information only and is not part of ANSI/AWWA C602.*

I. Introduction.

I.A. *Background.* Cement–mortar lining provides the interior of a ferrous-metal pipe with a smooth finish that protects it from corrosion and tuberculation. The lining can significantly retard the recurrence of these problems in previously used pipe if the pipe has been properly cleaned and repaired before application of the lining. Furthermore, the lining can increase the pipeline’s carrying capacity because of the reduction in friction resulting from streamlining surface irregularities.

The use of cement mortar as a protective lining for water mains was reported by the French Academy of Science in 1836. Fourteen years later, cement-lined, coated sheet-metal pipe was introduced in the United States. Some of the early pipelines were in use for the better part of a century, but it was not until the 1930s that a practical method was developed for lining pipe in place.

The first field trial of in-place cement–mortar lining (of pipe that had been in service) was conducted in Jersey City, N.J., in 1933. The pipe was a short section 72 in. (1,830 mm) in diameter. The favorable outcome of the trial led to the cleaning and lining of more than 27,000 ft (8,230 m) of aged 48-in. (1,220-mm) riveted-steel pipe supplying Newark, N.J. The lining stopped all leakage and, as a result of streamlining the surface over large rivets, also increased the Hazen-Williams flow coefficient by 14 points (estimated by the engineer).

For many years, the smallest-diameter pipe that could be reconditioned by the centrifugal process was 24 in. (600 mm) because a man was required to ride the lining machine through the pipe. In 1950, a remote-control centrifugal-lining machine was introduced that made in-place lining of progressively smaller-diameter pipe possible. Presently, pipelines ranging from 4 in. (100 mm) to 28 ft (9.2 m) in diameter can be cleaned and cement–mortar lined in place.

I.B. *History.* The first American Water Works Association (AWWA) standard for cement–mortar lining of pipe in place was published in 1939 as part of AWWA C205-41 (formerly 7A-7-41), Cement–Mortar Protective Lining and Coating for Steel Water Pipe. That standard was primarily concerned with in-plant lining and coating, a completely different process from in-place lining. Therefore, in 1951, the in-place

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

lining portion was withdrawn and expanded into a separate standard under the direction of the late H.A. Price, who authored most of the new document. That standard, AWWA C602, Cement–Mortar Lining of Water Pipelines in Place—Sizes 16 In. and Larger, was approved as tentative in 1954 and made standard in 1955.

In 1962, Price suggested to the AWWA Steel Water Pipe Manufacturers Technical Advisory Committee (SWPMTAC) that AWWA C602-55 should be revised in view of the extended competence of the centrifugal-lining process, which at that time included pipe as small as 4 in. (100 mm) in diameter. The assignment was given to SWPMTAC Subcommittee 8 and resulted in the revision of the standard adopted and published in 1967.

In 1972, the standard was again considered for revision to reflect the state of the art of in-place cement–mortar lining. The more frequent use of in-place cement–mortar lining in new large-diameter steel pipelines prompted the committee to note some of the standard procedures used in this application. The standard was revised in 1976, 1983, 1988, 1995, 2000, 2006, 2011, and 2017. This edition was approved on Jan. 12, 2023.

I.C. Acceptance. In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the Water Research Foundation (formerly AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). The American Water Works Association (AWWA) and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.[†] Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. Specific policies of the state or local agency.
2. Four standards developed under the direction of NSF:[‡] NSF/ANSI/CAN[§] 60, Drinking Water Treatment Chemicals—Health Effects; NSF/ANSI/CAN 61, Drinking Water System Components—Health Effects; NSF/ANSI/CAN 372, Drinking Water

[†] Persons outside the United States should contact the appropriate authority having jurisdiction.

[‡] NSF International, 789 North Dixboro Road, Ann Arbor, MI 48105.

[§] Standards Council of Canada, 55 Metcalfe Street, Suite 600, Ottawa, ON K1P 6L5 Canada.

System Components—Lead Content; and NSF/ANSI/CAN 600, Health Effects Evaluation and Criteria for Chemicals in Drinking Water.

3. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,⁴ and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI/CAN 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdictions. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

NSF/ANSI/CAN 600 (which formerly appeared in NSF/ANSI/CAN 60 and 61 as Annex A, “Toxicology Review and Evaluation Procedures”) does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of NSF/ANSI/CAN 600 procedures may not always be identical, depending on the certifier.

ANSI/AWWA C602 does not address additives requirements. Thus, users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues. This standard has no applicable information for this section.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives.* The following information should be provided by the purchaser:

1. Standard used—that is, ANSI/AWWA C602, Cement–Mortar Lining of Water Pipelines in Place—4 In. (100 mm) and Larger, of latest revision.

⁴ Both publications available from National Academy of Sciences, 500 Fifth Street, NW, Washington, DC 20001.

2. Project. Diameter, length, and location of pipeline, including plan and profile drawings when available; limits of pipeline shutdowns, if service requirements make these limits necessary; location of access manholes; location, type, and size of valves; location of interconnecting pipelines, hydrant branches, and service pipes; location of fittings and restrictions that could interfere with cleaning and lining operations; location, diameter, and connections of temporary bypass, if required; and other details of the pipe within the scope of the contract between the purchaser and the constructor.

3. Services provided by purchaser. Description of services or field operations to be performed by the purchaser, such as locating the main to be cleaned and lined; removal and replacement of line valves; operation of valves; tagging valves that separate the main to be cleaned and lined from the water system to prevent accidental opening; shutting off inflow of water from connecting pipelines; locating and operating blowoffs; connecting and disconnecting temporary bypasses to customer services; obtaining permits required for the work; handling customer contacts; disinfection; and conducting flow tests.

4. Additional work to be performed by constructor. Description of work, including repairs to deteriorated pipe; extra thickness of lining over the rivet heads and lockbar seams; excavation, backfill, and resurfacing work at access excavations; method of opening and closing access openings in the pipeline; supplying, laying, and removing temporary bypass pipe; and operation of main-line or blowoff valves.

NOTE: When it is necessary to repair deteriorated pipe before lining, the pipe will be repaired by the purchaser or under provisions of the contract between the purchaser and the constructor.

5. Water for cleaning and lining operations. Location of water sources, method of supplying, quantity available, and pressure information.

6. Disposal of cleaning water and debris. Requirements for the disposal of cleaning water, old lining, and other debris; instructions regarding permits from the responsible authorities.

7. Permissible cement–mortar materials. Preference for, or any restrictions on, type of cement or admixtures to be used in lining mortar.

8. Purchaser options. Options that may be specified by the purchaser after reviewing the following items in the sections noted:

- a. Whether compliance with NSF/ANSI/CAN 61, Drinking Water System Components—Health Effects, is required.
- b. Details of federal, state, provincial, territorial, and local requirements (Sec. 4.3.1).

- c. Cement (Sec. 4.3.2).
- d. Use of admixtures (Sec. 4.3.3, Sec. 4.4.1, and Sec. 4.4.2).
- e. Mortar lining thickness (Sec. 4.4.5).
- f. Access openings (Sec. 4.5.1).
- g. Traffic control (Sec. 4.5.1).
- h. Surface finish (Sec. 4.5.4).
- i. Cleaning of valves; new bolts and gaskets (Sec. 4.5.6.1 and Sec. 4.5.6.2).
- j. Curing by purchaser (Sec. 4.5.7.3).
- k. Temporary bypass to customers (Sec. 4.6).
- l. Disinfection of temporary bypass (Sec. 4.6.2).
- m. Leaking valves (Sec. 4.7.2).
- n. Access openings for lining for new pipe (Sec. 4.8.1).
- o. Surface finish for new pipe (Sec. 4.8.4).
- p. Affidavit of compliance (Sec. 6.3).

III.B. *Modification to Standard.* Any modification to the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. The major changes made to the standard in this edition include the following:

- 1. Updated Sec. I.C., Acceptance, in the foreword with the latest Standards Council language reflecting the addition of reference to NSF/ANSI/CAN 372 and 600.
- 2. In Sec. 3, Definitions, the definition of potable water was added.
- 3. Updated Sec. 4.3.1, Materials, with the latest Standards Council boilerplate language.
- 4. Sec. 4.3.2 was revised to include ASTM C595/C595M Type IL cement as an option.

V. Comments. If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services at 303.794.7711; write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098; or email at standards@awwa.org.

This page intentionally blank.



**American Water Works
Association**

Dedicated to the World's Most Important Resource®

ANSI/AWWA C602-23
(Revision of ANSI/AWWA C602-17)

AWWA Standard



Cement–Mortar Lining of Water Pipelines in Place—4 In. (100 mm) and Larger

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes the requirements for the materials and application of a cement–mortar lining to the inside surface of 4-in. (100-mm) and larger new and old steel, ductile-iron, and cast-iron water pipelines that have been previously installed, as well as related work. The application requirements are that the lining of straight pipe sections and long-radius bends shall be performed by a machine that progresses uniformly through the pipe, applies cement mortar against the pipe surfaces, and is provided with an attachment for mechanically troweling the mortar to obtain a smooth lining of uniform thickness with smooth transitions over joints, and that the lining of bends, specials, and areas adjacent to valves shall be machine sprayed and hand troweled or, where machine placement is impractical, shall be performed manually.

Sec. 1.2 Purpose

The purpose of this standard is to define the minimum requirements for cement–mortar lining of water pipelines, 4 in. (100 mm) and larger, in place, including materials, design, and methods for construction.