

## **BSI Standards Publication**

# **Granulated cork — Size analysis** by mechanical sieving



BS ISO 2030:2018 BRITISH STANDARD

## National foreword

This British Standard is the UK implementation of ISO 2030:2018.

The UK participation in its preparation was entrusted to Technical Committee PRI/81, Cork.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018 Published by BSI Standards Limited 2018

ISBN 978 0 580 98807 3

ICS 79.100

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2018.

Amendments/corrigenda issued since publication

Date Text affected

BS ISO 2030:2018

## INTERNATIONAL STANDARD

ISO 2030

Third edition 2018-10-12

## **Granulated cork — Size analysis by mechanical sieving**

Granulés de liège — Analyse granulométrique par tamisage mécanique



BS ISO 2030:2018 **ISO 2030:2018(E)** 



## COPYRIGHT PROTECTED DOCUMENT

## $\, @ \,$ ISO 2018, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Coı	ntents	Page
Fore	eword	iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	1
5	Apparatus	1
6	Sampling	1
7	Procedure 7.1 Test portion 7.2 Determination	2
8	Expression of results	2
9	Test report	2
Rihl	lingraphy	3

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>.

This document was prepared by Technical Committee ISO/TC 87, Cork.

This third edition cancels and replaces the second edition (ISO 2030:1990), of which it constitutes a minor revision. Minor editorial details have been introduced in this edition.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>.

## Granulated cork — Size analysis by mechanical sieving

## 1 Scope

This document specifies a method to obtain granule size distribution of granulated cork by mechanical sieving.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2067, Granulated cork — Sampling

### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <a href="https://www.iso.org/obp">https://www.iso.org/obp</a>
- IEC Electropedia: available at <a href="http://www.electropedia.org/">http://www.electropedia.org/</a>

## 4 Principle

Mechanical sieving of a test portion in specified conditions. Weighing of each portion of sieved material.

## 5 Apparatus

- **5.1 Screening column**, comprising:
- **5.1.1** Cover, which shall fit the sieves perfectly (see 5.1.2 and 5.1.3).
- **5.1.2 Sequence of sieves**, whose mesh apertures conform to the series ISO/R 40/3 (see ISO 565). The first sieve corresponds to the dimension just higher than the maximum wanted, the next to the last corresponds to the dimension just lower than the minimum wanted and the last corresponds to the dimension of the powder.
- **5.1.3 Base**, which shall fit the sieves perfectly (see 5.1.2).
- **5.1.4 Vibrator**, capable of producing 300 vertical vibrations of an amplitude of 5 mm/min and having a rotating speed of 1 r/min.
- **5.1.5 Balance**, accuracy 0,1 g.

### 6 Sampling

Sampling shall be carried out in accordance with ISO 2067.