

BS IEC 62899-202:2016



BSI Standards Publication

Printed electronics

Part 202: Materials — Conductive ink

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of IEC 62899-202:2016.

The UK participation in its preparation was entrusted to Technical Committee AMT/9, Printed Electronics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.

Published by BSI Standards Limited 2016

ISBN 978 0 580 87173 3

ICS 31.180; 87.080

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2016.

Amendments/corrigenda issued since publication

Date	Text affected
-------------	----------------------



INTERNATIONAL STANDARD

**Printed electronics –
Part 202: Materials – Conductive ink**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 31.180; 87.080

ISBN 978-2-8322-3197-5

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references.....	7
3 Terms and definitions	8
4 Atmospheric conditions for evaluation and conditioning	10
5 Evaluation of properties of conductive ink	10
5.1 Specimen.....	10
5.2 Contents	10
5.2.1 Solid content.....	10
5.2.2 Non-volatile content	10
5.2.3 Ash content.....	11
5.2.4 Foreign matter	11
5.3 Physical properties.....	12
5.3.1 Density	12
5.3.2 Rheology	12
5.3.3 Surface tension.....	13
5.3.4 Size of conductive materials.....	13
5.3.5 Flashpoint.....	15
5.3.6 Evaporation rate	15
6 Evaluation of the properties of a conductive layer.....	16
6.1 Test piece	16
6.1.1 General	16
6.1.2 Substrate	16
6.1.3 Conductive ink	16
6.1.4 Dimensions of test piece	16
6.1.5 Preparation of test piece	16
6.2 Electrical properties	16
6.2.1 Volume resistivity.....	16
6.2.2 Surface resistivity	21
6.3 Optical properties.....	22
6.3.1 Overview	22
6.3.2 Luminous transmittance	22
6.3.3 Chromaticity.....	22
6.3.4 Uniformity of colour.....	23
6.3.5 Haze.....	24
6.3.6 Refractive index.....	25
7 Storage	25
7.1 Storage conditions	25
7.2 Method for measuring aged deterioration	25
7.3 Report of the results.....	25
Annex A (informative) Examples of the four-point probe for applying an appropriate weight	26
A.1 Internal structure.....	26
A.2 Example of the general view.....	26

Annex B (informative) Equation of correction factor F	27
B.1 General.....	27
B.2 Conditions for correction factor F	27
B.3 Equation of correction factor F	28
Annex C (informative) Influence of the measuring position and the size of specimen on resistance.....	29
C.1 Influence of the measuring position on resistance	29
C.2 Influence of the size of the specimen on resistance.....	29
Bibliography	31
Figure 1 – Example of four-point probe measurement.....	17
Figure 2 – Example of four-probe measurement equipment.....	17
Figure 3 – Measuring positions of resistance (Type A).....	19
Figure 4 – Measuring positions of resistance (Type B).....	19
Figure 5 – Measuring positions of resistance (Type C).....	20
Figure A.1 – Example of the internal structure of probe.....	26
Figure A.2 – Example of the general view of the probe	26
Figure B.1 – Schematic diagram of the geometry of the conductive layer and the configuration of probes A, B, C, and D	27
Figure C.1 – Measurement model for the influence of the measuring position on sheet resistance.....	29
Figure C.2 – Model measurement of the influence of the specimen size	30
Table 1 – Resistance range of the test piece and the applied current	18
Table 2 – List of the size of the specimen.....	18

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PRINTED ELECTRONICS –

Part 202: Materials – Conductive ink

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62899-2-1 has been prepared by IEC technical committee 119: Printed electronics.

The text of this standard is based on the following documents:

FDIS	Report on voting
119/88/FDIS	119/101A/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 62899 series, published under the general title *Printed electronics*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

INTRODUCTION

The IEC 62899-20x series relates mainly to evaluation methods for materials of printed electronics. The series also include storage methods, packaging and marking, and transportation conditions.

The IEC 62899-20x series is divided into parts for each material. Each part is prepared as a generic specification containing fundamental information for the area of printed electronics.

The IEC 62899-20x series consists of the following parts:

Part 201: Materials – Substrates

Part 202: Materials – Conductive ink

Part 203: Materials – Semiconductor ink¹

(Subsequent parts will be prepared for other materials.)

Furthermore, sectional specifications, blank detail specifications, and detail specifications of each material will follow these parts.

This part of IEC 62899 is prepared for conductive materials used in printed electronics and contains the test conditions, the evaluation methods and the storage conditions.

¹ Under consideration.

PRINTED ELECTRONICS –

Part 202: Materials – Conductive ink

1 Scope

This part of IEC 62899 defines the terms and specifies the standard methods for characterisation and evaluation.

This International Standard is applicable to conductive inks and conductive layer that are made from conductive inks.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5-2, *Photography and graphic technology – Density measurements – Part 2: Geometric conditions for transmittance density*

ISO 5-3, *Photography and graphic technology – Density measurements – Part 3: Spectral conditions*

ISO 124, *Latex, rubber – Determination of total solids content*

ISO 291, *Plastics – Standard atmospheres for conditioning and testing*

ISO 304, *Surface active agents – Determination of surface tension by drawing up liquid films*

ISO 489:1999, *Plastics – Determination of refractive index*

ISO 758, *Liquid chemical products for industrial use – Determination of density at 20 degrees C*

ISO 1183-1, *Plastics – Methods for determining the density of non-cellular plastics – Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 2555, *Plastics – Resins in the liquid state or as emulsions or dispersions – Determination of apparent viscosity by the Brookfield Test method*

ISO 2592, *Determination of flash and fire points – Cleveland open cup method*

ISO 2719, *Determination of flash point – Pensky-Martens closed cup method*

ISO 2811-1, *Paints and varnishes – Determination of density – Part 1: Pycnometer method*

ISO 2811-2, *Paints and varnishes – Determination of density – Part 2: Immersed body (plummet) method*