
**Styrene-butadiene rubber (SBR) —
Determination of the microstructure
of solution-polymerized SBR —**

**Part 2:
FTIR with ATR method**

*Caoutchouc styrène-butadiène (SBR) — Détermination de la
microstructure du SBR polymérisé en solution —*

Partie 2: Méthode FTIR avec ATR



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	2
5 Calibration	2
5.1 FTIR.....	2
5.2 ATR.....	2
6 Sampling	2
7 Procedure for measuring ATR spectrum	2
8 Determination of the microstructure of butadiene and the styrene content	3
8.1 Measurement of the absorbance for each microstructure component.....	3
8.2 Calculation of microstructures.....	4
8.2.1 General.....	4
8.2.2 Base line correction of each absorbance peak.....	5
8.2.3 Ratio of absorbance.....	5
8.2.4 Second order terms.....	5
8.2.5 Styrene content and microstructures in mass % by regression formulae.....	5
8.2.6 Microstructures in mol %.....	6
9 Precision	6
10 Test report	6
Annex A (informative) Precision results from an interlaboratory test programme	8
Annex B (informative) Acquisition of regression formulae for microstructure	10
Annex C (informative) Determination of microstructure by NMR spectrometry	12
Bibliography	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This first edition of ISO 21561-2 cancels and replaces ISO 21561:2005, which has been technically revised. It also incorporates Amendment ISO 21561:2005/Amd.1:2010.

ISO 21561 consists of the following parts, under the general title *Styrene-butadiene rubber (SBR) — Determination of the microstructure of solution-polymerized SBR*:

- *Part 1: ¹H-NMR and IR with cast-film method*
- *Part 2: FTIR with ATR method*

Styrene-butadiene rubber (SBR) — Determination of the microstructure of solution-polymerized SBR —

Part 2: FTIR with ATR method

WARNING — Persons using this part of ISO 21561 should be familiar with normal laboratory practice. This part of ISO 21561 does not purport to address all the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

CAUTION — Certain procedures specified in this part of ISO 21561 might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This part of ISO 21561 specifies procedures for the quantitative determination of the microstructure of the butadiene and the content of styrene in solution-polymerized SBR (S-SBR) by Fourier Transform Infrared Spectrometry (FTIR) with Attenuated Total Reflection (ATR) method. The styrene content is expressed in mass % relative to the whole polymer. The vinyl, trans and cis contents are expressed in mol % relative to the butadiene content. This method is only applicable to raw rubbers.

NOTE 1 Precision as shown in [Annex A](#) may not be obtained for S-SBRs containing polystyrene block or styrene content more than 45 mass %.

NOTE 2 Only “vinyl”, “trans” and “cis”, are used in this part of ISO 21561. However, the expression of vinyl, trans and cis mean as follows in general:

- vinyl: vinyl unit, vinyl bond, 1,2-unit, 1,2-bond, 1,2-vinyl-unit or 1,2-vinyl-bond;
- trans: 1,4-trans unit, 1,4-trans bond, trans-1,4 unit or trans1,4 bond;
- cis: 1,4-cis unit, 1,4-cis bond, cis-1,4 unit or cis-1,4 bond.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1795, *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

3 Principle

The IR spectrum of the S-SBR sample is measured by FTIR with ATR. The absorbances that are characteristic of each microstructure component and styrene at the specified wavelengths are used to determine the content of each component by using the specific formulae presented in this part of ISO 21561.