

BS ISO 15901-1:2016



BSI Standards Publication

Evaluation of pore size distribution and porosity of solid materials by mercury porosimetry and gas adsorption

Part 1: Mercury porosimetry

bsi.

...making excellence a habit.™

National foreword

This British Standard is the UK implementation of ISO 15901-1:2016. It supersedes BS ISO 15901-1:2005 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee LBI/37, Particle characterization including sieving.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016.
Published by BSI Standards Limited 2016

ISBN 978 0 580 81558 4

ICS 19.120

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2016.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

**Evaluation of pore size distribution
and porosity of solid materials
by mercury porosimetry and gas
adsorption —**

Part 1:
Mercury porosimetry

*Evaluation de la distribution de taille des pores et la porosité des
matériaux solides par porosimétrie à mercure et l'adsorption des gaz —
Partie 1: Porosimétrie à mercure*



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	4
5 Principles	5
6 Apparatus and material	6
6.1 Sample holder.....	6
6.2 Porosimeter.....	7
6.3 Mercury.....	7
7 Procedures for calibration and performance	7
7.1 General.....	7
7.2 Pressure signal calibration.....	7
7.3 Volume signal calibration.....	7
7.4 Vacuum transducer calibration.....	7
7.5 Verification of porosimeter performance.....	8
8 Procedures	8
8.1 Sampling.....	8
8.1.1 Obtaining a test sample.....	8
8.1.2 Quantity of sample.....	8
8.2 Method.....	9
8.2.1 Sample pre-treatment.....	9
8.2.2 Filling of the sample holder and evacuation.....	9
8.2.3 Filling the sample holder with mercury.....	9
8.2.4 Measurement.....	10
8.2.5 Completion of test.....	10
8.2.6 Blank and sample compression correction.....	10
9 Evaluation	11
9.1 Determination of the pore size distribution.....	11
9.2 Determination of the specific pore volume.....	11
9.3 Determination of the specific surface area.....	12
9.4 Determination of the bulk and skeleton densities.....	12
9.5 Determination of the porosity.....	13
10 Reporting	13
Annex A (informative) Mercury porosimetry analysis results	14
Annex B (informative) Recommendations for the safe handling of mercury	17
Bibliography	19

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 24, *Particle characterization including sieving*, Subcommittee SC 4, *Particle characterization*.

This second edition cancels and replaces the first edition (ISO 15901-1:2005), which has been technically revised. It also incorporates the Corrigendum ISO 15901-1:2005/Cor 1:2007.

ISO 15901 consists of the following parts, under the general title *Evaluation of pore size distribution and porosity of solid materials by mercury porosimetry and gas adsorption*:

- *Part 1: Mercury porosimetry*
- *Part 2: Analysis of mesopores and macropores by gas adsorption*
- *Part 3: Analysis of micropores by gas adsorption*

Introduction

In general, different pores (micro-, meso-, and macropores) may be pictured as either apertures, channels or cavities within a solid body or as space (i.e. interstices or voids) between solid particles in a bed, compact or aggregate. Porosity is a term which is often used to indicate the porous nature of solid material and in this International Standard is more precisely defined as the ratio of the total pore volume of the accessible pores and voids to the volume of the particulate agglomerate. In addition to the accessible pores, a solid may contain closed pores which are isolated from the external surface and into which fluids are not able to penetrate. The characterization of closed pores is not covered in this International Standard.

Porous materials may take the form of fine or coarse powders, compacts, extrudates, sheets or monoliths. Their characterization usually involves the determination of the pore size distribution as well as the total accessible pore volume or porosity. For some purposes it is also necessary to study the pore shape and interconnectivity and to determine the internal and external specific surface area.

Porous materials have great technological importance, for example in the context of the following:

- controlled drug release;
- catalysis;
- gas separation;
- filtration including sterilization;
- materials technology;
- environmental protection and pollution control;
- natural reservoir rocks;
- building materials;
- polymers and ceramic.

It is well established that the performance of a porous solid (e.g. its strength, reactivity, permeability) is dependent on its pore structure. Many different methods have been developed for the characterization of pore structure. In view of the complexity of most porous solids, it is not surprising that the results obtained are not always in agreement and that no single technique can be relied upon to provide a complete picture of the pore structure. The choice of the most appropriate method depends on the application of the porous solid, its chemical and physical nature and the range of pore size.

The most commonly used methods are as follows:

- a) Mercury porosimetry, where the pores are filled with mercury under pressure. This method is suitable for many materials with pores in the approximate diameter range of 0,004 μm to 400 μm .
- b) Meso- and macropore analysis by gas adsorption, where the pores are characterized by adsorbing a gas, such as nitrogen at liquid nitrogen temperature. The method is used for pores in the approximate diameter range of 0,002 μm to 0,1 μm (2 nm to 100 nm).
- c) Micropore analysis by gas adsorption, where the pores are characterized by adsorbing a gas, such as nitrogen at liquid nitrogen temperature. The method is used for pores in the approximate diameter range of 0,4 nm to 2 nm.

Evaluation of pore size distribution and porosity of solid materials by mercury porosimetry and gas adsorption —

Part 1: Mercury porosimetry

WARNING — The use of this International Standard may involve hazardous materials, operations and equipment. This International Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this International Standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard describes a method for the evaluation of the pore size distribution and the specific surface area of pores in solids by mercury porosimetry according to the method of Ritter and Drake^{[1][2]}. It is a comparative test, usually destructive due to mercury contamination, in which the volume of mercury penetrating a pore or void is determined as a function of an applied hydrostatic pressure, which can be related to a pore diameter.

Practical considerations presently limit the maximum applied absolute pressure to about 400 MPa (60 000 psi) corresponding to a minimum equivalent pore diameter of approximately 4 nm. The maximum diameter is limited for samples having a significant depth due to the difference in hydrostatic head of mercury from the top to the bottom of the sample. For the most purposes, this limit can be regarded as 400 µm. The measurements cover inter-particle and intra-particle porosity. In general, without additional information from other methods it is difficult to distinguish between these porosities where they co-exist. The method is suitable for the study of most porous materials non-wettable by mercury. Samples that amalgamate with mercury, such as certain metals, e.g. gold, aluminium, copper, nickel and silver, can be unsuitable with this technique or can require a preliminary passivation. Under the applied pressure some materials are deformed, compacted or destroyed, whereby open pores may be collapsed and closed pores opened. In some cases it may be possible to apply sample compressibility corrections and useful comparative data may still be obtainable. For these reasons, the mercury porosimetry technique is considered to be comparative.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3165, *Sampling of chemical products for industrial use — Safety in sampling*

ISO 14488, *Particulate materials* — Sampling and sample splitting for the determination of particulate properties

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

porosimeter

instrument for measuring pore volume and pore size distribution