
**Plastics — Liquid resins —
Determination of density by the
pycnometer method**

*Plastiques — Résines liquides — Détermination de la masse
volumique par la méthode du pycnomètre*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	1
6 Procedure	2
6.1 Preparation of resin.....	2
6.2 Measurement of density.....	2
7 Expression of results	2
8 Test report	3
Bibliography	4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 1675:1985), which has been technically revised.

The main changes are as follows:

- the specification of the apparatus has been revised;
- a bibliography with references for the density of air and water has been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics — Liquid resins — Determination of density by the pycnometer method

1 Scope

This document specifies a method for the determination of the density of liquid resins using a pycnometer.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

density

ρ

ratio of the mass, m , of a sample to its volume, V , at temperature, T

Note 1 to entry: It is expressed in kg/m³, kg/dm³ (g/cm³) or kg/l (g/ml).

4 Principle

Determination of the mass of a resin contained in a pycnometer of known volume at 23 °C.

NOTE This method is easily applicable to low and medium viscosity resins. Difficulties in the procedure can arise for high viscosity resins.

5 Apparatus

5.1 Pycnometer, consisting of a graduated glass flask with a close-fitting ground glass stopper. Alternatively, the pycnometer may be closed with a ground glass stopper with a capillary tube which allows to set a given volume and escape of air bubbles at the same time.

The pycnometer may be equipped with a suitable funnel for easier filling.

The graduated or total volume of the pycnometer at $(23,0 \pm 0,1)$ °C, measured by determining the mass of distilled water filled in the pycnometer until the graduation mark or total volume at this temperature, shall have an accuracy of 0,01 % or better (see [Clause 7](#)).

5.2 Balance, accurate to 0,2 mg.

5.3 Thermostatic device, capable of being maintained at $(23,0 \pm 0,1)$ °C.