BS EN 16306:2013



BSI Standards Publication

Natural stone test methods — Determination of resistance of marble to thermal and moisture cycles

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW



BS EN 16306:2013 BRITISH STANDARD

National foreword

This British Standard is the UK implementation of EN 16306:2013.

The UK participation in its preparation was entrusted to Technical Committee B/545, Natural stone.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 75405 0

ICS 73.020; 91.100.15

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2013.

Amendments issued since publication

Date Text affected

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 16306

February 2013

ICS 73.020; 91.100.15

English Version

Natural stone test methods - Determination of resistance of marble to thermal and moisture cycles

Méthodes d'essai pour pierres naturelles - Détermination de la résistance du marbre aux cycles thermiques et d'humidité

Prüfverfahren für Naturstein - Bestimmungen der Beständigkeit von Marmor bei zyklischer Belastung mit Wärme und Feuchtigkeit

This European Standard was approved by CEN on 7 December 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents Page Foreword 3 2 3 Terms and definitions4 Principle......4 4 Symbols......5 5 6 Apparatus5 Preparation of specimens......9 7 Sampling......9 7.1 Test specimens9 7.2 7.3 Reference marks on the specimens ______10 7.4 8 Control measurements before cycling.......10 8.1 8.2 8.3 8.4 Calculation of results.......11 9 9.1 Bowing magnitude11 Flexural strength......11 9.2 10 Precision.......12 11 **A.1 A.2 B.1** General14 **B.2** Ultrasonic velocity14 **B.3** Modulus of elasticity......15 **C.1**

Foreword

This document (EN 16306:2013) has been prepared by Technical Committee CEN/TC 246 "Natural stones", the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2013, and conflicting national standards shall be withdrawn at the latest by August 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies a laboratory method for determining the resistance to thermal and moisture cycling of marble intended for cladding of building facades.

For scientific definition of marble, reference is made to EN 12670:2001, Terminology: 2.1.243 a.

NOTE Bowing and rapid strength loss is known to occur in some marbles when used as exterior claddings.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12372, Natural stone test methods – Determination of flexural strength under concentrated load

EN 12670:2001, Natural stone - Terminology

EN 13161, Natural stone test methods – Determination of flexural strength under constant moment

EN 14146, Natural stone test methods – Determination of the dynamic modulus of elasticity (by measuring the fundamental resonance frequency)

EN 14579, Natural stone test methods – Determination of sound speed propagation

EN ISO 4892-1:2000, Plastics - Methods of exposure to laboratory light sources - Part 1: General guidance (ISO 4892-1:1999)

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

bowing

change in shape from flat and planar to a curved or dished shape in a convex or concave direction

Note 1 to entry: Other terms commonly used for the same phenomenon are dishing and warping. Convex bowing is quantified by positive values, concave bowing by negative values.

3.2

convex

centre part of the specimen is bowing upwards, away from the moist substratum

3.3

concave

centre part of the specimen is bowing downwards, against the moist substratum

4 Principle

Bowing is measured on test samples exposed to moisture from beneath and heating from above. The temperature interval is from 20°C to 80°C, one cycle completed each 24 h. The 80 °C is measured on a black reference, placed on the surface of one specimen to control the climate of the chamber/bath.