



BSI Standards Publication

Leather — Pickled sheep pelts — Guidelines for grading on the basis of defect and size

National foreword

This British Standard is the UK implementation of ISO 17551:2018.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear & Leather.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018
Published by BSI Standards Limited 2018

ISBN 978 0 580 92996 0

ICS 59.140.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 28 February 2018.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
17551

First edition
2018-02-01

**Leather — Pickled sheep pelts —
Guidelines for grading on the basis of
defect and size**

*Cuir — Peaux de moutons picklées — Lignes directrices pour le
classement sur la base des défauts et de la taille*



Reference number
ISO 17551:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 General	1
5 Grading on the basis of defects	1
5.1 Grade I.....	1
5.2 Grade II.....	1
5.3 Grade III.....	2
5.4 Grade IV.....	2
5.5 Grade V.....	2
6 Tabular and graphical representation of the classification system	2
7 Grading on the basis of size	3
7.1 General.....	3
7.2 Extra large.....	3
7.3 Large.....	3
7.4 Medium.....	3
7.5 Small.....	3
7.6 Extra small.....	3

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 120, *Leather*, Subcommittee SC 1, *Raw hides and skins, including pickled pelts*.

Leather — Pickled sheep pelts — Guidelines for grading on the basis of defect and size

1 Scope

This document provides guidance for grading pickled sheep pelts based on size and defects.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 General

In general, pH requirement of pickled sheep pelts should be ascertained before grading. The pH of the pickled sheep pelt should be $2,0 \pm 0,2$.

For the purpose of the grading system, pickled sheep pelts are graded based on:

- a) defects;
- b) size.

5 Grading on the basis of defects

5.1 Grade I

Pickled sheep pelts of Grade I should have the following qualities:

- a) generally free from defects and damages;
- b) defects and damages not exceeding 10 % of the total area;
- c) free from defects like score marks, warble holes, meat, fat, pox marks, cockles;
- d) fleshy with good quality and fine grain.

Pickled sheep pelts that belong to Grade I but have a thinner skin should be regarded as Grade II.

5.2 Grade II

Pickled sheep pelts of Grade II should have the following qualities:

- a) defects and damages in the range of 11 % to 20 % of the total area;