



BSI Standards Publication

**Paper, board, pulps and cellulose
nanomaterials — Determination of
residue (ash content) on ignition at 525 °C**

National foreword

This British Standard is the UK implementation of ISO 1762:2019. It supersedes BS ISO 1762:2015, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PAI/11, Methods of test for paper, board and pulps.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 580 99087 8

ICS 85.040; 85.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 July 2019.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

INTERNATIONAL
STANDARD

ISO
1762

Fourth edition
2019-07-26

**Paper, board, pulps and cellulose
nanomaterials — Determination
of residue (ash content) on
ignition at 525 °C**

*Papier, carton et pâtes et nanomatériaux à base de cellulose —
Détermination du résidu (cendres) après incinération à 525 °C*



Reference number
ISO 1762:2019(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	3
6 Sampling and preparation of test specimen	3
6.1 Sample amount.....	3
6.2 Paper, board and pulp sampling.....	3
6.3 Cellulose nanomaterial sampling.....	3
7 Procedure	4
7.1 General.....	4
7.2 Measurement of moisture or dry matter content.....	4
7.3 Incineration.....	5
7.3.1 General.....	5
7.3.2 Incineration of paper, board and pulps.....	5
7.3.3 Incineration of cellulose nanomaterials.....	5
7.4 Measurement of residue (ash) mass.....	5
8 Expression of results	5
9 Test report	6
Annex A (informative) Precision	7
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This fourth edition cancels and replaces the third edition (ISO 1762:2015), which has been technically revised. The main changes compared to the previous edition are as follows:

- Scope revised to cover cellulose nanomaterials instead of only paper, board and pulps;
- A definition of cellulose nanomaterial, along with additional instructions for sampling, sample preparation, and incineration for cellulose nanomaterials have been incorporated;
- Additional instructions are given on how to express results when a sample has low ash content.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Paper, board, pulps and cellulose nanomaterials — Determination of residue (ash content) on ignition at 525 °C

1 Scope

This document describes the determination of the residue (ash content) on ignition of paper, board, pulps and cellulose nanomaterials at 525 °C. It is applicable to all types of paper, board, pulp and cellulose nanomaterial samples.

This document provides measurement procedures to obtain a measurement precision of 0,01 % or better for residue (ash content) on ignition at 525 °C.

Determination of residue (ash content) on ignition at 900 °C of paper, board, pulps and cellulose nanomaterials is described in ISO 2144.

In the context of this document, the term “cellulose nanomaterial” refers specifically to cellulose nano-object (see 3.2 to 3.4). Owing to their nanoscale dimensions, these cellulose nano-objects can have intrinsic properties, behaviours or functionalities that are distinct from those associated with paper, board and pulps.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 287, *Paper and board — Determination of moisture content of a lot — Oven-drying method*

ISO 638, *Paper, board and pulps — Determination of dry matter content — Oven-drying method*

ISO 7213, *Pulps — Sampling for testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1

residue on ignition ash content

ratio of the mass of the residue remaining after a test specimen of paper, board, pulp or cellulose nanomaterial (3.2) is ignited at 525 °C ± 25 °C to the oven-dry mass of the test specimen before ignition

Note 1 to entry: This property has been referred to as either “residue on ignition” or “ash content” in earlier editions of this document.