

---

---

**Paints and varnishes — Evaluation of  
properties of coating systems related  
to the spray application process —**

**Part 3:  
Assessment of sagging, formation of  
bubbles, pinholing and hiding power**

*Peintures et vernis — Évaluation des propriétés des systèmes de  
revêtement liées au mode d'application par pulvérisation —*

*Partie 3: Évaluation du festonnage, de la formation de bulles, des  
piqûres et du pouvoir masquant*





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Tendency to sagging</b> .....	<b>2</b>
4.1 General .....	2
4.2 Evaluation .....	4
<b>5 Bubbles</b> .....	<b>4</b>
5.1 General .....	4
5.2 Evaluation .....	4
<b>6 Pinholing</b> .....	<b>4</b>
6.1 General .....	4
6.2 Evaluation .....	4
<b>7 Hiding power</b> .....	<b>4</b>
7.1 General .....	4
7.2 Evaluation .....	5
<b>8 Test report</b> .....	<b>5</b>
<b>Annex A (informative) Examples of bubbles, pinholes and craters</b> .....	<b>6</b>
<b>Bibliography</b> .....	<b>14</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 139, *Paints and varnishes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 28199-3:2009), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the terms bubble formation limit and cratering have been moved from ISO 28199-1 to this document;
- assessment using measuring techniques was added for all evaluations;
- process hiding power (see [Clause 7](#)) was changed to hiding power;
- 3-D photographs and the associated profiles have been included for bubbles and pinholes;
- the normative references have been updated;
- the document has been editorially revised.

A list of all parts in the ISO 28199 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

In many areas (e.g. car manufacture, industrial coatings, coatings for plastics) the coating materials used are adapted to the specific application equipment and technologies of the particular user. A coating material is, therefore, to be understood as a semi-manufactured product that only receives its final form in combination with the specific application conditions. The adaptation to the application conditions is therefore decisive for the quality of the coated product.

The test methods specified in the ISO 28199 series are based on studies by a Working Group of the European Council for Automotive R&D (EUCAR).

They may be used for evaluation of coating materials in research, development and production with regard to their suitability and safety for industrial processes, and error analysis. The properties of coating materials and coatings to be evaluated depend on the film thickness, so a coating system of increasing thickness is applied to a test panel under defined conditions.

The following characteristics are measured (see ISO 28199-1):

- film thickness in accordance with ISO 2808;
- surface texture;
- colour in accordance with ISO 18314-1;
- mottling;
- gloss in accordance with ISO 2813.

The following properties are determined in combination with visual assessment or, if necessary, optical measurement techniques:

- colour stability/colour evaluation, process hiding power, re-dissolving, overspray absorption, wetting, surface texture and mottling (see ISO 28199-2);
- tendency to sagging, formation of bubbles, pinholing and hiding power (this document).



# Paints and varnishes — Evaluation of properties of coating systems related to the spray application process —

## Part 3:

## Assessment of sagging, formation of bubbles, pinholing and hiding power

**IMPORTANT** — The electronic file of this document contains colours which are considered to be useful for the correct understanding of the document. Users should therefore consider printing this document using a colour printer.

### 1 Scope

This document specifies visual methods for the assessment of tendency to sagging, formation of bubbles, pinholing and hiding power of coating materials applied to a test panel under defined conditions, using spray application process. Assessment using measuring techniques is also described for all evaluations.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6504-3, *Paints and varnishes — Determination of hiding power — Part 3: Determination of hiding power of paints for masonry, concrete and interior use*

ISO 28199-1:2021, *Paints and varnishes — Evaluation of properties of coating systems related to the spray application process — Part 1: Vocabulary and preparation of test panels*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 28199-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### **bubble formation limit**

start of a number of bubbles, agreed between the interested parties, in a measurement field

Note 1 to entry: A single bubble does not define the bubble formation limit. Bubbles at the edge of the measuring area and in the perforated area of the panel (see [Figure 1](#)) should not be taken into account.

#### 3.2

##### **cratering**

formation in a film or coating of small circular depressions that persist after drying/curing

Note 1 to entry: Craters can extend into deeper layers of a coating or into the substrate.