



| | | |
|--|-----------------------------------|---------------|
| AEROSPACE MATERIAL SPECIFICATION | AMS7287™ | REV. A |
| | Issued 2012-08 Revised 2022-09 | |
| Superseding AMS7287 | | |
| (R) Fluorocarbon Elastomer (FKM) High Temperature/HTS Oil Resistant/Fuel Resistant Low Compression Set/70 to 80 Hardness, Low Temperature Tg -22 °F (-30 °C), for Seals in Oil/Fuel/Specific Hydraulic Systems | | |

RATIONALE

Update to latest AMS7xxx template.

1. SCOPE

1.1 Form

This specification covers a high temperature, compression set, and fluid resistant fluorocarbon (FKM) elastomer in the form of molded O-rings, molded compression seals, molded O-ring cord, and molded-in-place gaskets for aeronautical and aerospace applications. For sheet, strip, tubing, extrusions, and molded shapes, use the AMS3384 specification.

1.2 Application

These products are expected to be suitable for use in contact with air and a wide variety of fuels, lubricants, specific hydraulic fluids, and a variety of gas turbine engine lubricants, including higher thermo-oxidative stability (HTS) lubricants, including those conforming to MIL-PRF-23699 Class HTS, MIL-PRF-7808 Grade 4, MIL-PRF-83282, and AS5780 Class HPC; however, usage is not limited to such applications. This material type has a typical service temperature range of -40 to +400 °F (-40 to +204 °C). These products are not suitable for use in phosphate ester based hydraulic fluids. Each application should be considered individually. It is the responsibility of the user to determine that this specification is appropriate for the environments (temperature range, fluids exposure, etc.) in which it is sought to be used.

1.3 Order of Precedence

Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained. This specification is in addition to and in no way limiting, superseding, or abrogating any contractual obligation as required by the applicable procurement document. In the event of conflict in requirements, the order of precedence shall be:

1. Procurement document or contractual agreement and all statutory and regulatory requirements (excluding this document).
2. Applicable purchaser's drawing or SAE ASXXXX parts standard.
3. Specification referenced on the drawing.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS7287A/>