



BSI Standards Publication

Collection, logistics & treatment requirements for WEEE

Part 3-3: Specification for de-pollution - WEEE containing CRTs and flat panel displays

National foreword

This Published Document is the UK implementation of CLC/TS 50625-3-3:2017.

The UK participation in its preparation was entrusted to Technical Committee GEL/111, Electrotechnical environment committee.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2017
Published by BSI Standards Limited 2017

ISBN 978 0 580 96856 3

ICS 31.120; 13.030.99

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 September 2017.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

TECHNICAL SPECIFICATION
SPÉCIFICATION TECHNIQUE
TECHNISCHE SPEZIFIKATION

CLC/TS 50625-3-3

August 2017

ICS 13.030.99; 31.120

English Version

Collection, logistics & treatment requirements for WEEE - Part 3-3: Specification for de-pollution - WEEE containing CRTs and flat panel displays

Exigences de collecte, logistique et traitement pour les déchets d'équipements électriques et électroniques (DEEE)
- Partie 3-3: Spécifications relatives à la dépollution - DEEE contenant des tubes cathodiques et des écrans plats

Sammlung, Logistik und Behandlung von Elektro- und Elektronik-Altgeräten (WEEE) - Teil 3-3: Spezifikation der Schadstoffentfrachtung - WEEE mit CRT und Flachbildschirmgeräten

This Technical Specification was approved by CENELEC on 2017-06-19.

CENELEC members are required to announce the existence of this TS in the same way as for an EN and to make the TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

European foreword.....	5
Introduction.....	6
1 Scope	7
2 Normative references	7
3 Terms and definitions	8
4 De-pollution monitoring	8
4.1 Introduction.....	8
4.2 Target value methodology.....	8
4.3 Mass Balance methodology	8
4.4 Analysis methodology	9
4.101 Monitoring methodology	9
4.101.1 Introduction.....	9
4.101.2 CRT equipment	9
4.101.3 Flat Panel Display (FPD).....	10
5 Overview of the applicable methodologies - Applicable methodologies	10
6 Large appliances	10
7 Cooling and freezing appliances	10
8 CRT Display / FPD appliances.....	11
8.1 Introduction.....	11
8.2 CRT display appliances – Target value methodology	11
8.3 CRT display appliances – Analysis methodology	11
8.3.101 Residual CRT glass in CRT fractions	11
8.3.102 Fluorescent coating remaining on cleaned CRT glass.....	12
8.3.103 Lead content in separated panel glass	12
8.4 FPD appliances – Mass balance methodology	12
8.4.101 Introduction.....	12
8.4.102 Procedure	13
8.4.103 Results	13
8.5 FPD appliances – Analysis methodology.....	14
9 Lamps – introduction and analysis methodology.....	14
10 Small appliances	14

11	Protocol for components removed during a batch process	15
11.1	General procedure	15
11.2	Capacitors	15
11.3	Batteries	15
	Annex A (normative) Sampling protocol for the physically smallest non-metallic mechanical treatment fraction.....	16
	Annex B (normative) Sampling protocol for plastics	17
	Annex C (normative) Targets	18
	Annex D (informative) Target calculation example – Calculation example for large appliance.....	19
	Annex AA (normative) CRT and FPD: Sampling protocol	20
AA.1	Introduction.....	20
AA.2	Sample number and size	20
AA.2.1	Deflection coils and electron canons from CRT treatment	20
AA.2.2	Ferrous metal fraction from CRT treatment	20
AA.2.3	Sampling procedure for lead oxide analysis on panel glass	20
	Table 102 — Sample size for lead oxide analysis on panel glass.....	21
AA.2.4	Sampling procedure for the sulphur analysis on cleaned CRT glass	21
AA.2.5	Sampling procedure for crushed or shredded mixed fractions from CRT and FPD	21
	Table 103 — Sample size for crushed or shredded mix fractions from CRT and FPD	21
AA.3	Principles of sampling and sample preparation	21
AA.4	Packaging, storing and sending of samples	21
	Annex BB (normative) CRT: Analysis protocol for residual CRT glass in CRT fractions	23
BB.1	Analysis	23
BB.2	Calculation of the residual CRT glass in fractions	23
	Annex CC (normative) CRT: Analysis protocol for fluorescent coating remaining on cleaned CRT glass	24
CC.1	Introduction.....	24
CC.2	Visual inspection protocol	24
CC.3	Chemical analysis protocol	24
CC.3.1	General.....	24
CC.3.2	Test portion preparation	25
CC.3.3	Leaching step	25
CC.3.4	Leaching procedure	25
CC.3.5	Quantification technique.....	25
CC.3.6	Sulphur standard	26
	Annex DD (normative) CRT: Analysis protocol for the lead oxide in separated panel glass.....	27
DD.1	General.....	27
DD.2	Analysis by XRF method (onsite analysis).....	27
DD.3	Analysis by XRF method (laboratory analysis)	28

DD.4	Analysis by ICP OES method	28
DD.5	Reporting.....	28
Annex EE (normative)	FPD: Main steps for Mass Balance	29
EE.1	Preparation of the reference batch.....	29
EE.2	Treatment of the reference batch for a manual treatment process.....	29
EE.3	Calculation for manual treatment.....	29
EE.3.1	Description of the parameters	29
EE.3.2	Formulas	29
EE.4	Calculation and validation for mechanical treatment	30
EE.4.1	Description of the parameters	30
EE.4.2	Formulas	30
Figure 102	— Relation between parameters described in EE.4.1 and formula's given in EE.4.2.....	30
Annex FF (normative)	FPD: Analysis of the de-polluted physically smallest shredded mix fraction of flat panel displays	31
FF.1	Principles.....	31
FF.2	Verification.....	31
FF.3	Test portion preparation.....	31
FF.4	Mineralisation	32
FF.5	Analytical technique	32
Annex GG (informative)	CRT: Background on analysis protocol for fluorescent coating remaining on cleaned CRT glass.....	33
Bibliography	34

European foreword

This document (CLC/TS 50625-3-3:2017) has been prepared by CLC/TC 111X “Environmental aspects for electrical and electronic products and systems”.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CENELEC by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

EN 50625 is currently composed of the following parts:

- EN 50625-1, *Collection, logistics and Treatment requirements for WEEE — Part 1: General treatment requirements*;
- EN 50625-2-1, *Collection, logistics and Treatment requirements for WEEE — Part 2-1: Treatment requirements for lamps*;
- CLC/TS 50625-3-1, *Collection, logistics and treatment requirements for WEEE — Part 3-1: Specification for de-pollution — General*;
- CLC/TS 50625-3-3, *Collection, logistics and treatment requirements for WEEE — Part 3-3: WEEE containing CRTs and flat panel displays* [the present document].

This document has been prepared under mandate M/518 given to CENELEC by the European Commission and the European Free Trade Association.

This CLC/TS 50625-3-3 is to be used in conjunction with CLC/TS 50625-3-1.

This CLC/TS 50625-3-3 supplements or modifies the corresponding clauses in CLC/TS 50625-3-1, so as to convert that publication into the TS: Treatment specification for de-pollution - WEEE containing CRTs and flat panel displays.

When a particular subclause of CLC/TS 50625-3-1 is not mentioned in this CLC/TS 50625-3-3, that subclause applies as far as it is reasonable. When this standard states “addition”, “modification” or “replacement”, the relevant text in CLC/TS 50625-3-1 is to be adapted accordingly.

NOTE The following numbering system is used:

— subclauses, tables and figures that are numbered starting from 101 are additional to those in CLC/TS 50625-3-1;

— unless notes are in a new subclause or involve notes in Part 1, they are numbered starting from 101, including those in a replaced clause or subclause;

— additional annexes are lettered AA, BB, etc.

Introduction

In order to support EN 50625-2-2 *Treatment requirements for WEEE containing CRTs and flat panel displays* and thereby fulfil the requirement of the European Commission's Mandate M/518, it is necessary to include normative requirements (such as target and limit values for the analysis) into a document, which is able to be revised in the future, to take into account both practical experiences and changes in treatment technologies.

1 Scope

Clause 1 of CLC/TS 50625-3-1:2015 is replaced with the following:

This European Technical Specification is intended to be used in conjunction with *Collection, logistics and treatment requirements for WEEE — Part 1: General treatment requirements*, EN 50625-1, *Collection, logistics and Treatment requirements for WEEE — Part 2-2: Treatment requirements for WEEE containing CRTs and flat panel displays*, EN 50625-2-2 and *Collection, logistics and treatment requirements for WEEE — Part 3-1: Specification for de-pollution — General*, CLC/TS 50625-3-1.

2 Normative references

Clause 2 of CLC/TS 50625-3-1:2015 is replaced with the following:

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11885, *Water quality — Determination of selected elements by inductively coupled plasma optical emission spectrometry (ICP-OES)*

EN ISO 12846, *Water quality - Determination of mercury - Method using atomic absorption spectrometry (AAS) with and without enrichment (ISO 12846)*

EN 13657, *Characterization of waste - Digestion for subsequent determination of aqua regia soluble portion of elements*

EN 13656, *Characterization of waste - Microwave assisted digestion with hydrofluoric (HF), nitric (HNO₃) and hydrochloric (HCl) acid mixture for subsequent determination of elements*

EN 14899, *Characterization of waste - Sampling of waste materials - Framework for the preparation and application of a Sampling Plan*

EN 15002, *Characterization of waste - Preparation of test portions from the laboratory sample*

EN 15309, *Characterization of waste and soil - Determination of elemental composition by X-ray fluorescence*

ISO 16772, *Soil quality — Determination of mercury in aqua regia soil extracts with cold-vapour atomic spectrometry or cold-vapour atomic fluorescence spectrometry*

EN ISO 17294-2, *Water quality - Application of inductively coupled plasma mass spectrometry (ICP-MS) - Part 2: Determination of selected elements including uranium isotopes (ISO 17294-2)*

ISO/IEC 17025:2005, *General requirements for the competence of testing and calibration laboratories*

ISO 17852, *Water quality — Determination of mercury — Method using atomic fluorescence spectrometry*

EN 50625-1, *Collection, logistics & Treatment requirements for WEEE - Part 1: General treatment requirements*

CLC/TS 50625-3-1, *Collection, logistics & treatment requirements for WEEE - Part 3-1: Specification for de-pollution - General*