
**Carbon fibre — Determination of
density**

Fibre de carbone — Détermination de la masse volumique





COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Test specimens — General requirements	1
5 Conditioning and test conditions	2
6 Test methods	2
6.1 Method A: Liquid-displacement method.....	2
6.1.1 Principle.....	2
6.1.2 Apparatus and materials.....	2
6.1.3 Test specimen.....	3
6.1.4 Procedure.....	3
6.1.5 Expression of results.....	4
6.2 Method B: Sink/float method.....	5
6.2.1 Principle.....	5
6.2.2 Apparatus and materials.....	5
6.2.3 Test specimens.....	5
6.2.4 Procedure.....	6
6.2.5 Expression of results.....	6
6.3 Method C: Density-gradient column.....	6
6.3.1 Principle.....	6
6.3.2 Apparatus and materials.....	6
6.3.3 Test specimens.....	7
6.3.4 Procedure.....	7
6.4 Method D: Gas pycnometer method.....	8
6.4.1 Principle.....	8
6.4.2 Apparatus and materials.....	8
6.4.3 Test specimens.....	9
6.4.4 Procedure.....	9
7 Precision	10
8 Test report	10
Annex A (normative) Preparation of the density-gradient column	11
Annex B (normative) Calibration of the measurement cell and expansion cell	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

This third edition cancels and replaces the second edition (ISO 10119:2002), which has been technically revised.

The main changes compared to the previous edition are as follows:

- gas pycnometer method (method D) has been added;
- the calibration of the measurement cell and expansion cell have been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Density is a parameter that characterizes the basic physical properties of carbon fibre, and is also an important parameter for calculating the tensile strength and tensile modulus of carbon fibre.

ISO 10119:2002 describes three methods (A, B and C) of using liquid to determine the density of carbon fibre. In this edition, the gas pycnometer method is added as method D.

Gas pycnometer method uses inert gas instead of liquids to measure the volume of fibres, powders and cellular materials so as to obtain the density. The method give a much higher resolution (i.e. a factor of 100 times better).

With the development of electronic technology, fully automatic instruments are commercially available, which allow faster throughput testing which are suitable for large scale testing. In addition, there is no environmental pollution because no organic solvent is used.

Carbon fibre — Determination of density

1 Scope

This document specifies four methods for the determination of the density of carbon fibre tested as a yarn:

- method A: liquid-displacement method;
- method B: sink/float method;
- method C: density-gradient column method;
- method D: gas pycnometer method.

Method C is the reference method in cases of dispute, etc.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 1675, *Plastics — Liquid resins — Determination of density by the pycnometer method*

ISO 10548, *Carbon fibre — Determination of size content*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

density

mass per unit volume of a substance at a specified temperature

Note 1 to entry: This property is expressed in grams per cubic centimetre or in kilograms per cubic metre at the specified temperature. The recommended temperature is 23 °C.

4 Test specimens — General requirements

Test specimens shall be taken from desized samples unless otherwise agreed between the supplier and the customer. To remove the size, use the solvent extraction, chemical digestion or pyrolysis method specified in ISO 10548. The determination of the density may also be carried out on sized fibre by agreement between customer and supplier. The density of sized fibre may be taken to be identical to that of unsized fibre when the size content is low.