

BS EN ISO 1927-4:2012



BSI Standards Publication

Monolithic (unshaped) refractory products

Part 4: Determination of
consistency of castables

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW

raising standards worldwide™



National foreword

This British Standard is the UK implementation of EN ISO 1927-4:2012. It supersedes BS EN 1402-4:2003, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee RPI/1, Refractory products and materials.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2012.
Published by BSI Standards Limited 2012.

ISBN 978 0 580 65759 7

ICS 81.080

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 January 2013.

Amendments issued since publication

Date	Text affected
------	---------------

English Version

Monolithic (unshaped) refractory products - Part 4:
Determination of consistency of castables (ISO 1927-4:2012)

Produits réfractaires monolithiques (non façonnés) - Partie
4: Détermination de la consistance des bétons (ISO 1927-
4:2012)

Ungeformte (monolithische) feuerfeste Erzeugnisse - Teil 4:
Bestimmung der Konsistenz von Feuerbetonen (ISO 1927-
4:2012)

This European Standard was approved by CEN on 30 November 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 1927-4:2012) has been prepared by Technical Committee ISO/TC 33 "Refractories" in collaboration with Technical Committee CEN/TC 187 "Refractory products and materials" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2013, and conflicting national standards shall be withdrawn at the latest by June 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 1402-4:2003.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 1927-4:2012 has been approved by CEN as a EN ISO 1927-4:2012 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	2
5 Procedure	4
5.1 Determination of the consistency of insulating castables for rodding and tamping	4
5.2 Determination of the consistency of castables by tap flow table method	5
5.3 Determination of the consistency of dense vibrating castables by cone vibration method	5
5.4 Determination of the consistency of self-flowing castables	6
6 Test report	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1927-4 was prepared by Technical Committee ISO/TC 33, *Refractories*.

ISO 1927 consists of the following parts, under the general title *Monolithic (unshaped) refractory products*:

- *Part 1: Introduction and classification*
- *Part 2: Sampling for testing*
- *Part 3: Characterization as received*
- *Part 4: Determination of consistency of castables*
- *Part 5: Preparation and treatment of test pieces*
- *Part 6: Measurement of physical properties*
- *Part 7: Tests on pre-formed shapes*
- *Part 8: Determination of complementary properties*

Monolithic (unshaped) refractory products —

Part 4: Determination of consistency of castables

1 Scope

This part of ISO 1927 describes methods for the determination and measurement of the consistency of dense and insulating castables as defined in ISO 1927-1. It is applicable to all types of dense regular castables, dense deflocculated castables and insulating castables to determine the liquid addition necessary for preparing test pieces according to ISO 1927-5.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1927-1, *Monolithic (unshaped) refractory products — Part 1: Introduction and classification*

ISO 1927-5:2012, *Monolithic (unshaped) refractory products — Part 5: Preparation and treatment of test pieces*

3 Principle

The amount of water used in a castable mix for preparing test pieces has a significant influence on the test results. Excess water can reduce strength, increase shrinkage, and can cause sedimentation. Insufficient moisture can give voids due to poor compaction, with subsequent lower density and strength.

This part of ISO 1927 describes three different methods for determining the consistency according to the type of material:

- a) determination of the consistency of insulating castables containing significant amounts of light-weight aggregates such as vermiculite or perlite which would be destroyed by intensive mixing; such products are normally installed by pouring, rodding, tamping;
- b) determination of the consistency of all types of vibratable castables;
- c) determination of the consistency of self-flowing castables.

To obtain reproducible results, the following factors are closely controlled:

- wet mixing time;
- batch size, which is chosen for the required number of determinations (e.g. if determination of working time is required), and is also related to mixer pan size or bowl;
- mixer pan size adapted to batch weight to have at least 50 % and a maximum of 75 % volume loading by the dry batch;
- temperature (of the water, castable and mix and ambient temperature), of 18 °C to 22 °C for consistency and working time determination;
- quantity of water addition used in the test which is rapidly affected when the dry volume loading of the mixer pan drops below 50 % of the total dry capacity, due to the increased metal surface to be wetted;