INTERNATIONAL STANDARD

ISO 11127-2

Third edition 2020-10

Preparation of steel substrates before application of paints and related products — Test methods for nonmetallic blast-cleaning abrasives —

Part 2:

Determination of particle size distribution

Préparation des subjectiles d'acier avant application de peintures et de produits assimilés — Méthodes d'essai pour abrasifs non métalliques destinés à la préparation par projection —

Partie 2: Analyse granulométrique



ISO 11127-2:2020(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Cor	itents	Page
Fore	word	iv
1	Scope	1
2	Normative references	
3	Terms and definitions	
4	Apparatus	1
5	Sampling	2
6	Procedure	
7	Expression of results	3
8	Test report	3
Anne	ex A (informative) International Standards for non-metallic blast-cleaning abrasives	4
Bibli	iography	5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 139, *Paint and Varnishes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 11127-2:2011), which has been technically revised.

The main changes to the previous edition are as follows:

- the use of a sample divider or riffler has been introduced in <u>Clause 6</u>;
- Annex A has been updated.

A list of all parts in the ISO 11127 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives —

Part 2:

Determination of particle size distribution

1 Scope

This document specifies a method for the determination of the particle size distribution of non-metallic blast-cleaning abrasives by sieving.

This document is a part of the ISO 11127 series dealing with the sampling and testing of non-metallic abrasives for blast-cleaning.

The types of non-metallic abrasive and requirements for each are contained in the ISO 11126 series.

The ISO 11126 and ISO 11127 series have been drafted as a coherent set of International Standards on non-metallic blast-cleaning abrasives. Information on all parts of both series is given in <u>Annex A</u>.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 565:1990, Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings

ISO 11127-1, Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 1: Sampling

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at http://www.electropedia.org/

4 Apparatus

Ordinary laboratory apparatus and glassware, together with the following.

4.1 Test sieves, circular, with a height of between 25 mm and 50 mm and a sieving area approximately 200 mm in diameter, made of woven metal wire cloth. The frame of the test sieves shall be made of metal. The range of nominal mesh apertures depends on the specification for the product to be tested and shall comply with the requirements of ISO 565:1990, Table 2, as indicated in <u>Table 1</u>. The sieves shall have square openings. A lid and a residue pan shall also be provided.